

Plastical UX

Fujifilm Sericol PANTONE® Matching System

Version 2.1

- SMS Base Colors



SERICOL
More than ink...Solutions.

FUJIFILM

Plastical UX

Seritone Matching System

PANTONE® Shades Simulated From Seritone Base Colors

This booklet furnishes the necessary formulas to simulate all the "C" colors of the PANTONE Color Formula Guide, except Double print, Fluorescent, and Metallic Colors.

Each formula was printed through a 380.34.TW (153/cm) monofilament screen with a 80 durometer sharp edge squeegee, without thinning, on Leneta Opacity Cards. All formulas are presented by weight. However, due to variations in ink film thickness, screen mesh, and other variables, some formulas may need adjustments.

The Seritone Matching System (SMS) has been designed to enable screen printers to simulate almost any shade from nine SMS Base Colors plus Shading Black, Tinting White, and Mixing Clear.

Each SMS Base Color has been carefully selected for its cleanliness of tone, resistance to fading, and suitability for intermixing. In addition, each ink has been formulated to be free of lead and other heavy metals.

Although every care is taken in producing these formulations, variations in substrates and printing conditions will affect color achieved. Fujifilm Sericol USA Inc. assumes no responsibility for actual color achieved. For this reason, all formulations must be proofed, prior to production run, to ensure color accuracy.

In some cases, to accurately simulate a PANTONE shade, considerable amounts of Mixing Clear and/or Tinting White are in the formulation. The exterior durability of color mixes with high percentages of Mixing Clear and/or Tinting White will be reduced. The Technical Services Department, in many cases, can provide an alternate PANTONE simulation formula yielding improved exterior durability.

The SMS Base Colors are listed below and are available in single gallon containers:

DESCRIPTION	
UX-064SMS Yellow GS (Green Shade)	UX-165 SMS Magenta
UX-066 SMS Yellow RS (Red Shade)	UX-230 SMS Blue
UX-114 SMS Orange	UX-325 SMS Green
UX-121 SMS Red YS (Yellow Shade)	UX-TW SMS Tinting White
UX-127 SMS Violet	UX-SB SMS Shading Black
UX-164 SMS Red BS (Blue Shade)	UX-MX SMS Mixing Clear

Fujifilm Sericol USA Inc's color mixing ink formulations for screen process printing produce only simulations of PANTONE Colors in this color reproduction method due to differences in ink film, opacity and pigment selection. The pigment selection used in blending screen process inks may cause metamerism. Pantone, Inc. assumes no responsibility for formula accuracy. PANTONE® is Pantone, Inc.'s checkstandard trademark for color. Portions© Pantone, Inc., 1963,1991.C=Coated Paper

Plastical UX

PANTONE Yellow C UX-064 100.00	Formula	PANTONE Yellow 012 C UX-064 97.00 UX-TW 3.00	Formula	PANTONE Orange 021 C UX-114 81.17 UX-066 16.97 UX-TW 1.86	Formula	PANTONE Warm Red C UX-TW 38.31 UX-121 34.63 UX-114 19.37 UX-MX 7.69	Formula
PANTONE Red 032 C UX-114 36.71 UX-165 34.20 UX-MX 19.45 UX-TW 9.64	Formula	PANTONE Rubine Red C UX-165 79.03 UX-114 15.34 UX-TW 5.63	Formula	PANTONE Rhodamine Red C UX-165 46.77 UX-TW 41.99 UX-MX 9.07 UX-121 2.17	Formula	PANTONE Purple C UX-165 50.29 UX-MX 44.33 UX-230 2.49 UX-TW 2.10 UX-127 0.79	Formula
PANTONE Violet C UX-165 51.21 UX-MX 19.91 UX-230 13.94 UX-TW 13.10 UX-325 1.84	Formula	PANTONE Blue 072 C UX-230 51.62 UX-127 38.47 UX-MX 6.68 UX-164 3.08 UX-TW 0.15	Formula	PANTONE Reflex Blue C UX-230 70.68 UX-127 26.49 UX-TW 2.83	Formula	PANTONE Process Blue C UX-230 43.65 UX-MX 36.86 UX-TW 17.76 UX-325 1.73	Formula
PANTONE Green C UX-325 64.82 UX-TW 25.12 UX-MX 9.32 UX-064 0.74	Formula	PANTONE Black C UX-SB 45.80 UX-066 30.98 UX-TW 19.56 UX-127 3.66	Formula	PANTONE Process Yellow C UX-064 67.00 UX-TW 33.00	Formula	PANTONE Process Magenta C UX-165 56.97 UX-TW 35.81 UX-121 7.22	Formula

Plastical UX

PANTONE Process Cyan C UX-TW 75.16 UX-230 21.88 UX-325 2.96	Formula	PANTONE Process Black C UX-SB 45.80 UX-066 31.00 UX-TW 19.50 UX-127 3.70	Formula	PANTONE 100 C UX-TW 57.31 UX-MX 27.38 UX-064 15.14 UX-325 0.17	Formula	PANTONE 101 C UX-TW 41.40 UX-MX 30.00 UX-064 28.33 UX-325 0.27	Formula
PANTONE 102 C UX-064 74.77 UX-MX 20.50 UX-TW 4.42 UX-325 0.31	Formula	PANTONE 103 C UX-064 96.59 UX-164 2.41 UX-230 1.00	Formula	PANTONE 104 C UX-064 89.25 UX-TW 6.56 UX-325 2.53 UX-127 1.66	Formula	PANTONE 105 C UX-064 71.97 UX-TW 19.66 UX-325 4.56 UX-127 3.81	Formula
PANTONE 106 C UX-TW 47.58 UX-MX 29.67 UX-064 22.65 UX-325 0.10	Formula	PANTONE 107 C UX-064 39.64 UX-MX 33.76 UX-TW 26.50 UX-325 0.10	Formula	PANTONE 108 C UX-064 52.06 UX-MX 27.40 UX-TW 20.54	Formula	PANTONE 109 C UX-064 75.71 UX-MX 17.65 UX-TW 6.15 UX-165 0.49	Formula
PANTONE 110 C UX-064 81.17 UX-MX 8.40 UX-TW 7.12 UX-165 2.14 UX-325 1.17	Formula	PANTONE 111 C UX-064 84.50 UX-TW 11.20 UX-325 2.30 UX-127 2.00	Formula	PANTONE 112 C UX-064 82.40 UX-TW 11.20 UX-325 3.40 UX-127 3.00	Formula	PANTONE 113 C UX-TW 44.09 UX-MX 28.33 UX-064 27.37 UX-121 0.21	Formula

Plastical UX

PANTONE 114 C		Formula
UX-TW	36.53	
UX-064	35.53	
UX-MX	27.65	
UX-121	0.29	

PANTONE 115 C		Formula
UX-064	37.49	
UX-TW	32.64	
UX-MX	29.26	
UX-114	0.41	
UX-121	0.20	

PANTONE 116 C		Formula
UX-064	57.56	
UX-MX	26.46	
UX-TW	14.40	
UX-114	1.43	
UX-121	0.15	

PANTONE 117 C		Formula
UX-064	88.55	
UX-TW	5.06	
UX-164	4.51	
UX-325	1.88	

PANTONE 118 C		Formula
UX-064	82.60	
UX-TW	6.99	
UX-164	6.64	
UX-325	3.77	

PANTONE 119 C		Formula
UX-064	63.46	
UX-TW	26.32	
UX-SB	9.25	
UX-121	0.97	

PANTONE 120 C		Formula
UX-TW	56.00	
UX-MX	27.10	
UX-064	16.25	
UX-114	0.65	

PANTONE 121 C		Formula
UX-TW	49.76	
UX-MX	28.75	
UX-064	21.01	
UX-121	0.48	

PANTONE 122 C		Formula
UX-TW	38.11	
UX-064	33.65	
UX-MX	27.35	
UX-121	0.89	

PANTONE 123 C		Formula
UX-064	38.19	
UX-TW	28.17	
UX-MX	21.73	
UX-066	9.56	
UX-114	2.35	

PANTONE 124 C		Formula
UX-064	85.53	
UX-TW	9.29	
UX-121	4.55	
UX-230	0.63	

PANTONE 125 C		Formula
UX-064	81.25	
UX-164	8.00	
UX-TW	7.45	
UX-325	3.30	

PANTONE 126 C		Formula
UX-064	73.28	
UX-TW	17.25	
UX-SB	7.32	
UX-121	2.15	

PANTONE 1205 C		Formula
UX-TW	66.37	
UX-MX	29.52	
UX-064	3.89	
UX-114	0.22	

PANTONE 1215 C		Formula
UX-TW	62.29	
UX-MX	27.77	
UX-064	9.27	
UX-114	0.67	

PANTONE 1225 C		Formula
UX-TW	63.40	
UX-064	21.30	
UX-066	13.30	
UX-114	2.00	

Plastical UX

PANTONE 1235 C	Formula
UX-064	27.12
UX-MX	26.46
UX-TW	21.10
UX-066	20.59
UX-114	4.73

PANTONE 1245 C	Formula
UX-064	72.06
UX-TW	22.12
UX-121	4.34
UX-230	1.48

PANTONE 1255 C	Formula
UX-064	73.17
UX-TW	18.01
UX-SB	6.01
UX-121	2.81

PANTONE 1265 C	Formula
UX-064	65.70
UX-SB	15.40
UX-TW	15.40
UX-121	3.50

PANTONE 127 C	Formula
UX-TW	55.89
UX-MX	29.07
UX-064	14.62
UX-165	0.42

PANTONE 128 C	Formula
UX-TW	46.67
UX-MX	29.04
UX-064	23.55
UX-165	0.64
UX-230	0.10

PANTONE 129 C	Formula
UX-TW	62.65
UX-064	36.01
UX-165	1.34

PANTONE 130 C	Formula
UX-064	79.40
UX-TW	16.71
UX-165	3.79
UX-230	0.10

PANTONE 131 C	Formula
UX-064	87.24
UX-164	7.30
UX-TW	4.59
UX-230	0.87

PANTONE 132 C	Formula
UX-064	83.34
UX-164	8.87
UX-TW	5.26
UX-230	2.53

PANTONE 133 C	Formula
UX-064	70.59
UX-SB	13.91
UX-TW	12.05
UX-165	3.45

PANTONE 134 C	Formula
UX-TW	55.78
UX-MX	29.04
UX-064	13.34
UX-114	1.84

PANTONE 135 C	Formula
UX-TW	64.23
UX-064	32.37
UX-114	3.40

PANTONE 136 C	Formula
UX-TW	48.60
UX-064	46.90
UX-114	4.50

PANTONE 137 C	Formula
UX-064	61.55
UX-TW	24.55
UX-114	10.73
UX-066	3.17

PANTONE 138 C	Formula
UX-064	84.32
UX-121	8.46
UX-TW	6.46
UX-230	0.76

Plastical UX

PANTONE 139 C	Formula
UX-064 79.65	
UX-TW 8.37	
UX-121 6.71	
UX-SB 5.27	

PANTONE 140 C	Formula
UX-064 62.75	
UX-TW 19.79	
UX-SB 12.75	
UX-121 4.71	

PANTONE 1345 C	Formula
UX-TW 61.80	
UX-MX 29.46	
UX-064 6.60	
UX-114 2.14	

PANTONE 1355 C	Formula
UX-TW 60.92	
UX-MX 25.66	
UX-064 10.27	
UX-114 3.15	

PANTONE 1365 C	Formula
UX-TW 46.86	
UX-MX 29.66	
UX-064 12.40	
UX-066 5.65	
UX-114 5.43	

PANTONE 1375 C	Formula
UX-064 50.34	
UX-TW 35.45	
UX-114 13.64	
UX-121 0.57	

PANTONE 1385 C	Formula
UX-064 75.80	
UX-TW 11.90	
UX-121 11.02	
UX-230 1.28	

PANTONE 1395 C	Formula
UX-064 70.08	
UX-TW 13.81	
UX-121 8.17	
UX-SB 7.94	

PANTONE 1405 C	Formula
UX-064 59.83	
UX-SB 16.33	
UX-TW 16.29	
UX-121 7.55	

PANTONE 141 C	Formula
UX-TW 67.93	
UX-064 30.02	
UX-165 1.92	
UX-230 0.13	

PANTONE 142 C	Formula
UX-TW 48.96	
UX-064 47.79	
UX-165 3.14	
UX-230 0.11	

PANTONE 143 C	Formula
UX-064 55.61	
UX-TW 40.29	
UX-165 3.96	
UX-230 0.14	

PANTONE 144 C	Formula
UX-064 80.49	
UX-TW 9.88	
UX-164 9.63	

PANTONE 145 C	Formula
UX-064 77.25	
UX-164 12.55	
UX-TW 9.30	
UX-230 0.90	

PANTONE 146 C	Formula
UX-064 82.11	
UX-164 14.60	
UX-230 2.86	
UX-TW 0.43	

PANTONE 147 C	Formula
UX-064 55.95	
UX-TW 23.29	
UX-SB 15.83	
UX-165 4.93	

Plastical UX

PANTONE 148 C	Formula
UX-TW	92.03
UX-064	5.51
UX-114	2.46

PANTONE 149 C	Formula
UX-TW	89.93
UX-064	6.79
UX-114	3.28

PANTONE 150 C	Formula
UX-TW	66.49
UX-066	14.01
UX-064	10.57
UX-114	8.93

PANTONE 151 C	Formula
UX-064	48.99
UX-114	32.22
UX-TW	17.70
UX-121	1.09

PANTONE 152 C	Formula
UX-064	73.75
UX-121	13.73
UX-TW	11.35
UX-325	1.17

PANTONE 153 C	Formula
UX-064	69.85
UX-121	14.00
UX-TW	13.78
UX-230	2.37

PANTONE 154 C	Formula
UX-066	61.21
UX-164	16.63
UX-TW	16.31
UX-325	5.85

PANTONE 1485 C	Formula
UX-TW	86.24
UX-066	8.57
UX-114	5.19

PANTONE 1495 C	Formula
UX-TW	56.70
UX-066	30.15
UX-114	13.15

PANTONE 1505 C	Formula
UX-066	57.70
UX-114	33.80
UX-TW	8.50

PANTONE 1525 C	Formula
UX-114	84.53
UX-064	10.69
UX-230	2.91
UX-TW	1.87

PANTONE 1535 C	Formula
UX-114	52.90
UX-064	26.20
UX-SB	11.80
UX-TW	9.10

PANTONE 1545 C	Formula
UX-114	50.70
UX-SB	42.40
UX-TW	6.90

PANTONE 155 C	Formula
UX-TW	93.79
UX-064	5.26
UX-165	0.95

PANTONE 156 C	Formula
UX-TW	86.01
UX-064	11.74
UX-165	2.14
UX-230	0.11

PANTONE 157 C	Formula
UX-TW	51.43
UX-064	41.13
UX-165	7.31
UX-230	0.13

Plastical UX

PANTONE 158 C	Formula
UX-064	64.98
UX-TW	20.31
UX-164	13.18
UX-121	1.53

PANTONE 159 C	Formula
UX-064	73.30
UX-165	18.20
UX-TW	7.43
UX-325	1.07

PANTONE 160 C	Formula
UX-064	66.93
UX-165	23.07
UX-TW	7.36
UX-230	2.64

PANTONE 161 C	Formula
UX-064	56.53
UX-SB	17.20
UX-164	16.08
UX-TW	10.19

PANTONE 1555 C	Formula
UX-TW	93.63
UX-114	5.62
UX-064	0.75

PANTONE 1565 C	Formula
UX-TW	83.80
UX-114	12.90
UX-064	3.30

PANTONE 1575 C	Formula
UX-TW	65.27
UX-114	25.45
UX-064	9.28

PANTONE 1585 C	Formula
UX-114	48.90
UX-TW	41.85
UX-064	9.25

PANTONE 1595 C	Formula
UX-066	59.34
UX-121	20.34
UX-TW	19.04
UX-230	1.28

PANTONE 1605 C	Formula
UX-066	49.30
UX-TW	25.50
UX-121	21.30
UX-230	3.90

PANTONE 1615 C	Formula
UX-066	45.84
UX-TW	27.07
UX-121	15.66
UX-SB	11.43

PANTONE 162 C	Formula
UX-TW	93.22
UX-MX	3.47
UX-114	2.65
UX-121	0.66

PANTONE 163 C	Formula
UX-TW	82.73
UX-114	16.63
UX-064	0.64

PANTONE 164 C	Formula
UX-TW	63.09
UX-114	35.28
UX-064	1.63

PANTONE 165 C	Formula
UX-114	59.69
UX-TW	40.00
UX-064	0.31

PANTONE 166 C	Formula
UX-066	55.93
UX-121	22.03
UX-TW	21.15
UX-325	0.89

Plastical UX

PANTONE 167 C	Formula
UX-066 48.39	
UX-TW 29.50	
UX-121 20.32	
UX-230 1.79	

PANTONE 168 C	Formula
UX-066 46.02	
UX-121 20.88	
UX-TW 17.38	
UX-SB 15.72	

PANTONE 1625 C	Formula
UX-TW 89.70	
UX-114 7.20	
UX-121 3.10	

PANTONE 1635 C	Formula
UX-TW 83.40	
UX-114 13.00	
UX-121 3.60	

PANTONE 1645 C	Formula
UX-TW 65.30	
UX-114 26.50	
UX-121 8.20	

PANTONE 1655 C	Formula
UX-114 56.30	
UX-TW 34.30	
UX-121 9.40	

PANTONE 1665 C	Formula
UX-114 42.40	
UX-TW 26.00	
UX-121 20.00	
UX-MX 10.40	
UX-325 1.20	

PANTONE 1675 C	Formula
UX-066 39.60	
UX-121 31.80	
UX-TW 25.30	
UX-230 3.30	

PANTONE 1685 C	Formula
UX-066 36.10	
UX-121 36.00	
UX-TW 22.00	
UX-230 5.90	

PANTONE 169 C	Formula
UX-TW 95.96	
UX-121 2.64	
UX-114 1.40	

PANTONE 170 C	Formula
UX-TW 74.64	
UX-114 9.25	
UX-MX 8.23	
UX-121 7.88	

PANTONE 171 C	Formula
UX-TW 53.65	
UX-114 30.64	
UX-121 15.71	

PANTONE 172 C	Formula
UX-114 49.47	
UX-TW 33.83	
UX-121 16.70	

PANTONE 173 C	Formula
UX-TW 35.11	
UX-114 34.34	
UX-121 28.93	
UX-325 1.62	

PANTONE 174 C	Formula
UX-121 37.72	
UX-114 34.24	
UX-TW 23.39	
UX-230 4.65	

PANTONE 175 C	Formula
UX-114 34.63	
UX-TW 31.45	
UX-SB 17.82	
UX-121 16.10	

Plastical UX

PANTONE 176 C	Formula
UX-TW	91.49
UX-121	4.40
UX-MX	3.30
UX-165	0.81

PANTONE 177 C	Formula
UX-TW	82.93
UX-121	15.21
UX-114	1.86

PANTONE 178 C	Formula
UX-TW	61.07
UX-121	24.38
UX-114	8.67
UX-MX	5.88

PANTONE 179 C	Formula
UX-121	43.41
UX-TW	42.85
UX-114	13.10
UX-325	0.64

PANTONE 180 C	Formula
UX-121	49.59
UX-TW	39.00
UX-114	8.17
UX-325	3.24

PANTONE 181 C	Formula
UX-114	33.43
UX-164	29.25
UX-TW	27.65
UX-325	9.67

PANTONE 1765 C	Formula
UX-TW	92.14
UX-121	5.13
UX-165	2.73

PANTONE 1775 C	Formula
UX-TW	63.03
UX-MX	25.60
UX-121	8.44
UX-165	2.93

PANTONE 1785 C	Formula
UX-MX	45.83
UX-121	23.08
UX-TW	22.85
UX-165	8.24

PANTONE 1788 C	Formula
UX-121	52.50
UX-TW	27.70
UX-MX	10.80
UX-165	9.00

PANTONE 1795 C	Formula
UX-121	43.35
UX-MX	23.43
UX-TW	19.40
UX-165	13.09
UX-325	0.73

PANTONE 1805 C	Formula
UX-121	55.06
UX-TW	41.45
UX-127	3.49

PANTONE 1815 C	Formula
UX-165	40.90
UX-114	35.80
UX-TW	13.00
UX-325	10.30

PANTONE 1767 C	Formula
UX-TW	95.09
UX-121	2.79
UX-165	2.12

PANTONE 1777 C	Formula
UX-MX	38.55
UX-TW	37.81
UX-121	14.79
UX-165	8.85

PANTONE 1787 C	Formula
UX-MX	44.56
UX-121	28.76
UX-165	13.65
UX-TW	13.03

Plastical UX

PANTONE 1797 C		Formula
UX-121	52.00	
UX-TW	23.50	
UX-165	16.70	
UX-MX	6.20	
UX-SB	1.60	

PANTONE 1807 C		Formula
UX-121	52.69	
UX-165	27.22	
UX-TW	14.69	
UX-325	5.40	

PANTONE 1817 C		Formula
UX-121	69.69	
UX-230	14.75	
UX-165	11.30	
UX-TW	4.26	

PANTONE 182 C		Formula
UX-TW	96.74	
UX-165	1.95	
UX-121	1.31	

PANTONE 183 C		Formula
UX-TW	85.85	
UX-121	9.07	
UX-165	5.08	

PANTONE 184 C		Formula
UX-MX	47.76	
UX-TW	23.59	
UX-121	18.35	
UX-165	10.30	

PANTONE 185 C		Formula
UX-121	58.00	
UX-165	19.00	
UX-TW	17.00	
UX-MX	6.00	

PANTONE 186 C		Formula
UX-165	50.13	
UX-114	38.68	
UX-TW	10.62	
UX-325	0.57	

PANTONE 187 C		Formula
UX-121	50.34	
UX-165	35.37	
UX-TW	10.32	
UX-325	3.97	

PANTONE 188 C		Formula
UX-165	42.02	
UX-114	30.91	
UX-TW	15.81	
UX-325	11.26	

PANTONE 189 C		Formula
UX-TW	89.42	
UX-165	3.96	
UX-MX	3.63	
UX-121	2.99	

PANTONE 190 C		Formula
UX-TW	54.45	
UX-MX	25.01	
UX-165	11.44	
UX-121	9.10	

PANTONE 191 C		Formula
UX-MX	44.03	
UX-165	21.66	
UX-121	17.39	
UX-TW	16.92	

PANTONE 192 C		Formula
UX-121	36.55	
UX-165	30.82	
UX-MX	21.76	
UX-TW	10.87	

PANTONE 193 C		Formula
UX-121	43.93	
UX-165	42.63	
UX-TW	11.42	
UX-325	2.02	

PANTONE 194 C		Formula
UX-165	37.57	
UX-121	36.12	
UX-TW	20.36	
UX-325	5.95	

Plastical UX

PANTONE 195 C		Formula
UX-164	43.63	
UX-TW	27.95	
UX-114	17.07	
UX-325	11.35	

PANTONE 1895 C		Formula
UX-TW	95.82	
UX-165	2.92	
UX-121	1.26	

PANTONE 1905 C		Formula
UX-TW	78.69	
UX-MX	11.40	
UX-165	6.57	
UX-121	3.34	

PANTONE 1915 C		Formula
UX-MX	41.10	
UX-165	25.55	
UX-TW	20.78	
UX-121	12.57	

PANTONE 1925 C		Formula
UX-165	46.14	
UX-MX	28.46	
UX-114	17.88	
UX-TW	7.52	

PANTONE 1935 C		Formula
UX-165	54.98	
UX-121	28.79	
UX-TW	16.03	
UX-325	0.20	

PANTONE 1945 C		Formula
UX-165	52.77	
UX-121	29.02	
UX-TW	15.38	
UX-325	2.83	

PANTONE 1955 C		Formula
UX-165	45.29	
UX-121	27.14	
UX-TW	22.91	
UX-325	4.66	

PANTONE 196 C		Formula
UX-TW	90.22	
UX-MX	5.59	
UX-165	2.96	
UX-064	1.23	

PANTONE 197 C		Formula
UX-TW	80.63	
UX-165	9.26	
UX-MX	5.41	
UX-064	4.70	

PANTONE 198 C		Formula
UX-TW	60.16	
UX-165	22.53	
UX-121	17.31	

PANTONE 199 C		Formula
UX-165	60.76	
UX-114	25.77	
UX-TW	13.47	

PANTONE 200 C		Formula
UX-165	59.68	
UX-066	24.43	
UX-164	14.46	
UX-SB	1.43	

PANTONE 201 C		Formula
UX-165	41.27	
UX-121	36.09	
UX-TW	17.52	
UX-325	5.12	

PANTONE 202 C		Formula
UX-121	36.26	
UX-165	35.15	
UX-TW	19.93	
UX-325	8.66	

PANTONE 203 C		Formula
UX-TW	95.05	
UX-165	4.12	
UX-121	0.69	
UX-SB	0.14	

Plastical UX

PANTONE 204 C	Formula
UX-TW	84.82
UX-165	11.79
UX-121	3.27
UX-SB	0.12

PANTONE 205 C	Formula
UX-TW	39.52
UX-MX	30.45
UX-164	17.93
UX-165	12.10

PANTONE 206 C	Formula
UX-165	45.65
UX-MX	25.71
UX-121	20.21
UX-TW	8.43

PANTONE 207 C	Formula
UX-165	64.38
UX-066	19.87
UX-TW	8.76
UX-MX	5.51
UX-325	1.48

PANTONE 208 C	Formula
UX-165	54.28
UX-066	18.20
UX-TW	12.87
UX-MX	10.71
UX-325	3.94

PANTONE 209 C	Formula
UX-165	50.02
UX-066	19.81
UX-TW	12.79
UX-MX	9.86
UX-325	7.52

PANTONE 210 C	Formula
UX-TW	81.71
UX-MX	10.08
UX-165	6.58
UX-121	1.63

PANTONE 211 C	Formula
UX-TW	45.90
UX-MX	39.12
UX-165	11.68
UX-121	3.30

PANTONE 212 C	Formula
UX-MX	36.76
UX-TW	35.84
UX-165	22.27
UX-121	5.13

PANTONE 213 C	Formula
UX-MX	38.95
UX-165	32.87
UX-TW	18.09
UX-121	10.09

PANTONE 214 C	Formula
UX-165	59.80
UX-TW	23.96
UX-121	16.08
UX-325	0.16

PANTONE 215 C	Formula
UX-165	56.23
UX-121	21.10
UX-TW	19.41
UX-325	3.26

PANTONE 216 C	Formula
UX-165	47.05
UX-121	26.61
UX-TW	16.32
UX-325	10.02

PANTONE 217 C	Formula
UX-TW	96.30
UX-165	3.54
UX-127	0.16

PANTONE 218 C	Formula
UX-TW	55.29
UX-MX	22.70
UX-165	20.33
UX-121	1.68

PANTONE 219 C	Formula
UX-165	43.07
UX-MX	41.18
UX-TW	10.39
UX-121	5.36

Plastical UX

PANTONE 220 C	Formula
UX-165	46.20
UX-164	43.70
UX-TW	7.00
UX-SB	3.10

PANTONE 221 C	Formula
UX-165	44.40
UX-164	44.20
UX-SB	5.80
UX-TW	5.60

PANTONE 222 C	Formula
UX-165	57.86
UX-SB	16.41
UX-TW	14.04
UX-114	11.69

PANTONE 223 C	Formula
UX-TW	79.05
UX-165	10.47
UX-MX	10.08
UX-121	0.40

PANTONE 224 C	Formula
UX-MX	48.70
UX-TW	30.02
UX-165	20.34
UX-121	0.94

PANTONE 225 C	Formula
UX-MX	55.17
UX-165	39.58
UX-121	3.01
UX-TW	2.24

PANTONE 226 C	Formula
UX-165	75.82
UX-MX	13.45
UX-TW	4.32
UX-121	4.08
UX-114	2.33

PANTONE 227 C	Formula
UX-165	80.00
UX-114	10.00
UX-TW	7.00
UX-325	2.03
UX-127	0.97

PANTONE 228 C	Formula
UX-165	68.17
UX-121	14.64
UX-TW	10.35
UX-325	6.84

PANTONE 229 C	Formula
UX-165	39.57
UX-121	31.37
UX-TW	20.82
UX-230	7.58
UX-325	0.66

PANTONE 230 C	Formula
UX-TW	81.81
UX-MX	10.71
UX-165	7.15
UX-121	0.33

PANTONE 231 C	Formula
UX-MX	49.21
UX-TW	26.04
UX-165	24.07
UX-121	0.68

PANTONE 232 C	Formula
UX-MX	49.29
UX-165	37.06
UX-TW	11.71
UX-121	1.94

PANTONE 233 C	Formula
UX-165	67.08
UX-TW	30.53
UX-121	2.39

PANTONE 234 C	Formula
UX-165	69.39
UX-TW	17.62
UX-121	9.27
UX-325	3.72

PANTONE 235 C	Formula
UX-165	60.88
UX-TW	15.69
UX-121	15.33
UX-325	8.10

Plastical UX

PANTONE 236 C	Formula
UX-TW	68.00
UX-MX	25.40
UX-165	6.60

PANTONE 237 C	Formula
UX-TW	79.91
UX-165	20.09

PANTONE 238 C	Formula
UX-MX	41.25
UX-165	29.79
UX-TW	28.96

PANTONE 239 C	Formula
UX-165	53.78
UX-MX	26.10
UX-TW	20.12

PANTONE 240 C	Formula
UX-165	69.00
UX-TW	29.80
UX-325	1.00
UX-230	0.20

PANTONE 241 C	Formula
UX-165	70.27
UX-TW	27.48
UX-325	2.25

PANTONE 242 C	Formula
UX-165	56.92
UX-TW	20.26
UX-121	12.56
UX-325	10.26

PANTONE 2365 C	Formula
UX-TW	70.83
UX-MX	26.31
UX-165	2.73
UX-127	0.13

PANTONE 2375 C	Formula
UX-MX	52.43
UX-TW	29.41
UX-165	17.66
UX-127	0.28
UX-230	0.22

PANTONE 2385 C	Formula
UX-MX	46.22
UX-165	34.64
UX-TW	18.22
UX-127	0.66
UX-230	0.26

PANTONE 2395 C	Formula
UX-165	56.95
UX-MX	27.15
UX-TW	12.99
UX-127	2.91

PANTONE 2405 C	Formula
UX-165	88.58
UX-TW	7.42
UX-127	2.23
UX-325	1.77

PANTONE 2415 C	Formula
UX-165	67.81
UX-TW	27.91
UX-127	2.66
UX-325	1.62

PANTONE 2425 C	Formula
UX-165	62.57
UX-TW	25.71
UX-SB	5.15
UX-127	4.86
UX-114	1.71

PANTONE 243 C	Formula
UX-TW	80.64
UX-MX	15.86
UX-165	3.18
UX-127	0.32

PANTONE 244 C	Formula
UX-TW	93.07
UX-165	6.39
UX-127	0.54

Plastical UX

PANTONE 245 C	Formula
UX-TW 60.22	
UX-MX 28.38	
UX-165 10.32	
UX-127 1.08	

PANTONE 246 C	Formula
UX-165 50.62	
UX-MX 25.96	
UX-TW 21.04	
UX-230 1.21	
UX-127 1.17	

PANTONE 247 C	Formula
UX-165 54.86	
UX-MX 23.45	
UX-TW 19.11	
UX-230 1.32	
UX-127 1.26	

PANTONE 248 C	Formula
UX-165 70.95	
UX-TW 26.59	
UX-230 2.46	

PANTONE 249 C	Formula
UX-165 60.37	
UX-TW 30.33	
UX-SB 8.38	
UX-230 0.92	

PANTONE 250 C	Formula
UX-TW 90.54	
UX-MX 7.51	
UX-165 1.34	
UX-127 0.61	

PANTONE 251 C	Formula
UX-TW 47.42	
UX-MX 45.72	
UX-165 5.01	
UX-127 1.85	

PANTONE 252 C	Formula
UX-MX 44.44	
UX-TW 37.32	
UX-165 15.82	
UX-127 2.42	

PANTONE 253 C	Formula
UX-165 71.50	
UX-MX 13.60	
UX-TW 10.00	
UX-230 4.10	
UX-127 0.80	

PANTONE 254 C	Formula
UX-165 61.11	
UX-MX 25.69	
UX-TW 7.61	
UX-230 3.38	
UX-127 2.21	

PANTONE 255 C	Formula
UX-165 48.79	
UX-TW 36.99	
UX-SB 8.95	
UX-127 5.27	

PANTONE 256 C	Formula
UX-TW 96.29	
UX-MX 2.14	
UX-127 0.82	
UX-165 0.75	

PANTONE 257 C	Formula
UX-TW 94.34	
UX-165 2.29	
UX-MX 1.91	
UX-127 1.46	

PANTONE 258 C	Formula
UX-TW 59.46	
UX-165 35.51	
UX-230 3.58	
UX-066 1.45	

PANTONE 259 C	Formula
UX-165 81.54	
UX-325 16.56	
UX-TW 1.90	

PANTONE 260 C	Formula
UX-165 61.11	
UX-325 17.60	
UX-164 13.53	
UX-TW 7.76	

Plastical UX

PANTONE 261 C	Formula
UX-165	50.03
UX-164	22.08
UX-325	19.22
UX-TW	8.67

PANTONE 262 C	Formula
UX-165	59.11
UX-066	19.78
UX-230	11.20
UX-TW	5.92
UX-SB	3.99

PANTONE 2562 C	Formula
UX-TW	79.76
UX-MX	16.14
UX-165	2.18
UX-127	1.92

PANTONE 2572 C	Formula
UX-TW	76.39
UX-MX	15.45
UX-165	4.83
UX-127	3.33

PANTONE 2582 C	Formula
UX-TW	36.40
UX-165	33.90
UX-MX	21.40
UX-127	4.70
UX-230	3.60

PANTONE 2592 C	Formula
UX-165	63.00
UX-MX	20.19
UX-TW	8.97
UX-230	7.84

PANTONE 2602 C	Formula
UX-165	63.58
UX-TW	16.89
UX-MX	11.78
UX-230	7.75

PANTONE 2612 C	Formula
UX-165	41.44
UX-TW	38.50
UX-127	15.74
UX-066	4.32

PANTONE 2622 C	Formula
UX-TW	60.74
UX-164	22.01
UX-127	10.22
UX-SB	7.03

PANTONE 2563 C	Formula
UX-TW	94.33
UX-165	3.09
UX-127	2.58

PANTONE 2573 C	Formula
UX-TW	85.68
UX-165	7.41
UX-127	5.84
UX-064	1.07

PANTONE 2583 C	Formula
UX-TW	68.95
UX-165	20.28
UX-127	10.16
UX-066	0.61

PANTONE 2593 C	Formula
UX-TW	40.39
UX-165	32.76
UX-127	14.69
UX-MX	10.87
UX-SB	1.29

PANTONE 2603 C	Formula
UX-165	46.17
UX-TW	35.37
UX-127	15.21
UX-SB	3.25

PANTONE 2613 C	Formula
UX-165	46.44
UX-TW	33.45
UX-127	15.38
UX-SB	4.73

PANTONE 2623 C	Formula
UX-165	50.18
UX-TW	20.67
UX-127	15.81
UX-SB	13.34

Plastical UX

PANTONE 2567 C	Formula
UX-TW	94.34
UX-127	3.75
UX-165	1.77
UX-230	0.14

PANTONE 2577 C	Formula
UX-TW	49.00
UX-MX	24.25
UX-165	22.12
UX-230	4.63

PANTONE 2587 C	Formula
UX-TW	52.00
UX-165	39.18
UX-230	7.02
UX-164	1.80

PANTONE 2597 C	Formula
UX-TW	30.38
UX-127	27.01
UX-MX	22.54
UX-165	19.86
UX-066	0.21

PANTONE 2607 C	Formula
UX-165	43.78
UX-TW	31.68
UX-127	24.54

PANTONE 2617 C	Formula
UX-TW	40.63
UX-165	29.73
UX-127	25.85
UX-SB	3.79

PANTONE 2627 C	Formula
UX-TW	34.10
UX-165	31.85
UX-127	24.03
UX-SB	10.02

PANTONE 263 C	Formula
UX-TW	84.41
UX-MX	14.60
UX-127	0.79
UX-230	0.20

PANTONE 264 C	Formula
UX-TW	82.57
UX-MX	14.28
UX-127	2.58
UX-230	0.57

PANTONE 265 C	Formula
UX-MX	44.00
UX-165	34.51
UX-TW	12.01
UX-230	9.48

PANTONE 266 C	Formula
UX-165	67.37
UX-230	16.89
UX-TW	15.06
UX-325	0.68

PANTONE 267 C	Formula
UX-165	68.20
UX-TW	16.00
UX-230	15.80

PANTONE 268 C	Formula
UX-127	44.65
UX-TW	34.64
UX-164	16.46
UX-165	4.25

PANTONE 269 C	Formula
UX-127	36.65
UX-TW	31.24
UX-121	20.67
UX-325	11.44

PANTONE 2635 C	Formula
UX-TW	89.50
UX-MX	7.94
UX-127	2.09
UX-230	0.47

PANTONE 2645 C	Formula
UX-TW	89.14
UX-MX	6.46
UX-127	3.76
UX-230	0.64

Plastical UX

PANTONE 2655 C	Formula
UX-TW	43.24
UX-MX	30.45
UX-165	20.41
UX-230	5.90

PANTONE 2665 C	Formula
UX-TW	41.34
UX-165	30.36
UX-MX	20.41
UX-230	7.89

PANTONE 2685 C	Formula
UX-165	64.84
UX-230	17.03
UX-MX	10.04
UX-TW	6.61
UX-325	1.48

PANTONE 2695 C	Formula
UX-TW	55.86
UX-127	27.82
UX-SB	11.02
UX-114	5.30

PANTONE 270 C	Formula
UX-TW	97.22
UX-127	1.95
UX-230	0.83

PANTONE 271 C	Formula
UX-TW	79.02
UX-165	10.55
UX-MX	5.42
UX-230	4.13
UX-164	0.88

PANTONE 272 C	Formula
UX-TW	86.48
UX-127	8.44
UX-230	3.36
UX-064	1.72

PANTONE 273 C	Formula
UX-127	50.68
UX-TW	23.80
UX-230	19.44
UX-325	6.08

PANTONE 274 C	Formula
UX-127	61.11
UX-325	15.58
UX-TW	13.14
UX-230	10.17

PANTONE 275 C	Formula
UX-127	52.52
UX-325	18.84
UX-064	15.89
UX-TW	6.91
UX-230	5.84

PANTONE 276 C	Formula
UX-064	37.09
UX-127	35.40
UX-325	19.71
UX-TW	7.80

PANTONE 2705 C	Formula
UX-TW	87.98
UX-MX	7.24
UX-127	3.12
UX-230	1.66

PANTONE 2715 C	Formula
UX-TW	33.35
UX-MX	32.95
UX-165	22.46
UX-230	11.24

PANTONE 2725 C	Formula
UX-TW	61.60
UX-165	24.50
UX-230	10.80
UX-127	3.10

PANTONE 2735 C	Formula
UX-TW	32.30
UX-127	21.50
UX-165	17.50
UX-230	15.70
UX-MX	13.00

PANTONE 2745 C	Formula
UX-165	74.70
UX-230	24.64
UX-TW	0.66

Plastical UX

PANTONE 2755 C	Formula
UX-127	46.28
UX-TW	24.28
UX-230	22.16
UX-325	7.28

PANTONE 2765 C	Formula
UX-127	60.17
UX-325	22.24
UX-TW	9.81
UX-230	7.78

PANTONE 2706 C	Formula
UX-TW	77.69
UX-MX	20.32
UX-230	1.00
UX-127	0.99

PANTONE 2716 C	Formula
UX-TW	74.84
UX-MX	19.57
UX-127	2.89
UX-230	2.70

PANTONE 2726 C	Formula
UX-TW	47.14
UX-165	34.58
UX-230	18.28

PANTONE 2736 C	Formula
UX-165	34.58
UX-TW	33.53
UX-230	25.27
UX-127	6.62

PANTONE 2746 C	Formula
UX-TW	36.93
UX-230	33.11
UX-127	29.96

PANTONE 2756 C	Formula
UX-TW	36.81
UX-127	28.48
UX-230	26.26
UX-066	8.45

PANTONE 2766 C	Formula
UX-127	27.92
UX-TW	27.09
UX-230	25.01
UX-066	19.98

PANTONE 2707 C	Formula
UX-TW	97.94
UX-230	1.32
UX-127	0.74

PANTONE 2717 C	Formula
UX-TW	95.33
UX-230	3.09
UX-127	1.58

PANTONE 2727 C	Formula
UX-TW	59.41
UX-230	31.88
UX-127	8.71

PANTONE 2747 C	Formula
UX-127	42.37
UX-230	41.12
UX-066	14.55
UX-TW	1.96

PANTONE 2757 C	Formula
UX-127	35.47
UX-230	34.11
UX-066	26.42
UX-TW	4.00

PANTONE 2767 C	Formula
UX-SB	56.90
UX-230	18.20
UX-TW	14.10
UX-127	10.80

PANTONE 2708 C	Formula
UX-TW	76.89
UX-MX	20.32
UX-230	1.72
UX-127	1.07

Plastical UX

PANTONE 2718 C	Formula
UX-TW	45.53
UX-MX	40.46
UX-230	9.00
UX-127	5.01

PANTONE 2728 C	Formula
UX-230	39.94
UX-TW	37.44
UX-127	16.95
UX-MX	5.67

PANTONE 2738 C	Formula
UX-230	70.60
UX-127	29.40

PANTONE 2748 C	Formula
UX-230	46.27
UX-127	27.34
UX-TW	22.21
UX-066	4.18

PANTONE 2758 C	Formula
UX-230	38.44
UX-127	29.65
UX-TW	19.38
UX-066	12.53

PANTONE 2768 C	Formula
UX-066	33.69
UX-127	29.91
UX-230	24.45
UX-TW	11.95

PANTONE 277 C	Formula
UX-TW	97.78
UX-230	1.52
UX-127	0.70

PANTONE 278 C	Formula
UX-TW	95.23
UX-230	3.47
UX-127	1.30

PANTONE 279 C	Formula
UX-TW	80.92
UX-230	15.09
UX-127	3.99

PANTONE 280 C	Formula
UX-230	51.30
UX-127	25.80
UX-TW	12.72
UX-066	9.51
UX-SB	0.67

PANTONE 281 C	Formula
UX-230	37.90
UX-127	26.99
UX-066	23.49
UX-TW	11.62

PANTONE 282 C	Formula
UX-066	38.91
UX-230	32.28
UX-127	25.43
UX-TW	3.38

PANTONE 283 C	Formula
UX-TW	77.36
UX-MX	18.97
UX-230	2.82
UX-127	0.85

PANTONE 284 C	Formula
UX-TW	71.62
UX-MX	19.71
UX-230	6.88
UX-127	1.79

PANTONE 285 C	Formula
UX-TW	46.83
UX-230	29.41
UX-MX	11.93
UX-165	11.83

PANTONE 286 C	Formula
UX-230	76.00
UX-127	13.90
UX-TW	10.10

Plastical UX

PANTONE 287 C	Formula
UX-230	65.00
UX-127	16.00
UX-TW	15.00
UX-SB	4.00

PANTONE 288 C	Formula
UX-230	59.75
UX-127	20.42
UX-066	11.55
UX-TW	8.28

PANTONE 289 C	Formula
UX-066	35.72
UX-127	32.88
UX-230	25.67
UX-TW	5.73

PANTONE 290 C	Formula
UX-TW	79.82
UX-MX	18.40
UX-230	1.39
UX-127	0.39

PANTONE 291 C	Formula
UX-TW	67.93
UX-MX	28.80
UX-230	2.68
UX-127	0.59

PANTONE 292 C	Formula
UX-TW	65.29
UX-MX	27.68
UX-230	5.79
UX-127	1.24

PANTONE 293 C	Formula
UX-230	77.90
UX-TW	15.73
UX-127	6.37

PANTONE 294 C	Formula
UX-230	60.19
UX-TW	22.04
UX-127	10.25
UX-066	7.52

PANTONE 295 C	Formula
UX-230	52.73
UX-TW	19.25
UX-066	15.45
UX-127	12.57

PANTONE 296 C	Formula
UX-066	36.11
UX-230	32.02
UX-TW	16.71
UX-127	15.16

PANTONE 2905 C	Formula
UX-TW	96.06
UX-230	3.32
UX-127	0.62

PANTONE 2915 C	Formula
UX-TW	90.34
UX-230	8.69
UX-127	0.97

PANTONE 2925 C	Formula
UX-TW	76.48
UX-230	21.15
UX-127	2.01
UX-066	0.36

PANTONE 2935 C	Formula
UX-230	77.91
UX-TW	15.73
UX-127	6.36

PANTONE 2945 C	Formula
UX-230	73.62
UX-TW	14.86
UX-127	7.85
UX-064	1.84
UX-SB	1.83

PANTONE 2955 C	Formula
UX-230	65.43
UX-TW	13.63
UX-SB	10.81
UX-127	7.05
UX-064	3.08

Plastical UX

PANTONE 2965 C	Formula
UX-230	47.94
UX-SB	33.22
UX-TW	10.23
UX-127	5.85
UX-064	2.76

PANTONE 297 C	Formula
UX-TW	95.43
UX-230	4.09
UX-127	0.48

PANTONE 298 C	Formula
UX-TW	83.91
UX-230	10.71
UX-MX	4.74
UX-127	0.64

PANTONE 299 C	Formula
UX-TW	73.69
UX-230	21.18
UX-MX	4.16
UX-127	0.97

PANTONE 300 C	Formula
UX-230	67.99
UX-TW	29.69
UX-127	2.32

PANTONE 301 C	Formula
UX-230	63.60
UX-TW	27.77
UX-066	4.77
UX-127	3.86

PANTONE 302 C	Formula
UX-230	52.16
UX-TW	23.02
UX-066	17.47
UX-127	7.35

PANTONE 303 C	Formula
UX-230	39.98
UX-066	34.40
UX-TW	12.84
UX-127	12.78

PANTONE 2975 C	Formula
UX-TW	97.86
UX-230	1.86
UX-127	0.28

PANTONE 2985 C	Formula
UX-TW	76.56
UX-MX	13.86
UX-230	9.37
UX-127	0.21

PANTONE 2995 C	Formula
UX-TW	74.89
UX-230	25.11

PANTONE 3005 C	Formula
UX-230	58.89
UX-TW	40.32
UX-127	0.79

PANTONE 3015 C	Formula
UX-230	56.99
UX-TW	39.02
UX-066	2.72
UX-127	1.27

PANTONE 3025 C	Formula
UX-230	56.49
UX-TW	24.73
UX-114	9.98
UX-066	8.80

PANTONE 3035 C	Formula
UX-230	52.68
UX-114	23.08
UX-TW	18.50
UX-066	5.74

PANTONE 304 C	Formula
UX-TW	97.80
UX-230	2.10
UX-127	0.10

Plastical UX

PANTONE 305 C	Formula
UX-TW 95.07	
UX-230 4.83	
UX-127 0.10	

PANTONE 306 C	Formula
UX-TW 59.07	
UX-MX 27.42	
UX-230 12.46	
UX-325 1.05	

PANTONE 307 C	Formula
UX-230 64.94	
UX-MX 14.49	
UX-TW 10.73	
UX-325 9.84	

PANTONE 308 C	Formula
UX-230 82.49	
UX-066 11.17	
UX-325 3.22	
UX-TW 3.12	

PANTONE 309 C	Formula
UX-230 55.85	
UX-114 19.22	
UX-TW 14.88	
UX-066 10.05	

PANTONE 310 C	Formula
UX-TW 93.95	
UX-230 4.87	
UX-325 1.18	

PANTONE 311 C	Formula
UX-TW 79.25	
UX-230 9.15	
UX-MX 8.32	
UX-325 3.28	

PANTONE 312 C	Formula
UX-TW 60.43	
UX-230 20.49	
UX-MX 11.48	
UX-325 7.60	

PANTONE 313 C	Formula
UX-TW 45.91	
UX-230 32.84	
UX-325 12.53	
UX-MX 8.72	

PANTONE 314 C	Formula
UX-230 49.08	
UX-TW 29.54	
UX-325 13.07	
UX-MX 5.62	
UX-066 2.69	

PANTONE 315 C	Formula
UX-230 50.10	
UX-TW 28.94	
UX-064 8.87	
UX-325 6.28	
UX-SB 5.81	

PANTONE 316 C	Formula
UX-230 32.00	
UX-TW 25.78	
UX-SB 22.22	
UX-325 11.00	
UX-064 9.00	

PANTONE 3105 C	Formula
UX-TW 92.37	
UX-230 3.35	
UX-MX 2.73	
UX-325 1.55	

PANTONE 3115 C	Formula
UX-TW 85.96	
UX-230 6.79	
UX-325 4.71	
UX-MX 2.54	

PANTONE 3125 C	Formula
UX-TW 72.60	
UX-230 14.52	
UX-325 10.73	
UX-MX 2.15	

PANTONE 3135 C	Formula
UX-TW 48.26	
UX-230 29.28	
UX-325 21.03	
UX-MX 1.43	

Plastical UX

PANTONE 3145 C	Formula
UX-TW	41.71
UX-230	35.60
UX-325	18.18
UX-064	3.28
UX-MX	1.23

PANTONE 3155 C	Formula
UX-230	51.19
UX-TW	27.75
UX-066	12.88
UX-325	8.18

PANTONE 3165 C	Formula
UX-TW	33.49
UX-325	29.78
UX-230	24.00
UX-SB	12.73

PANTONE 317 C	Formula
UX-TW	98.38
UX-230	1.04
UX-325	0.58

PANTONE 318 C	Formula
UX-TW	96.05
UX-230	2.15
UX-325	1.80

PANTONE 319 C	Formula
UX-TW	67.26
UX-MX	23.59
UX-325	5.05
UX-230	4.10

PANTONE 320 C	Formula
UX-325	36.74
UX-MX	29.55
UX-230	23.85
UX-TW	9.86

PANTONE 321 C	Formula
UX-230	36.34
UX-325	31.78
UX-MX	27.91
UX-064	3.97

PANTONE 322 C	Formula
UX-230	44.17
UX-MX	28.58
UX-066	16.60
UX-TW	10.65

PANTONE 323 C	Formula
UX-230	57.20
UX-066	26.63
UX-TW	11.78
UX-325	4.39

PANTONE 324 C	Formula
UX-TW	97.27
UX-230	1.89
UX-064	0.84

PANTONE 325 C	Formula
UX-TW	90.45
UX-230	4.85
UX-325	3.20
UX-064	1.50

PANTONE 326 C	Formula
UX-TW	70.36
UX-325	16.25
UX-230	11.15
UX-064	2.24

PANTONE 327 C	Formula
UX-325	41.59
UX-TW	30.37
UX-230	24.44
UX-064	3.60

PANTONE 328 C	Formula
UX-230	40.71
UX-TW	28.03
UX-325	17.42
UX-064	13.84

PANTONE 329 C	Formula
UX-230	41.29
UX-TW	20.29
UX-325	19.64
UX-066	18.78

Plastical UX

PANTONE 330 C	Formula
UX-TW 32.15	
UX-230 30.15	
UX-066 26.84	
UX-SB 10.86	

PANTONE 3242 C	Formula
UX-TW 94.99	
UX-325 3.74	
UX-230 1.27	

PANTONE 3252 C	Formula
UX-TW 88.44	
UX-325 9.38	
UX-230 2.18	

PANTONE 3262 C	Formula
UX-TW 79.54	
UX-325 16.87	
UX-230 3.59	

PANTONE 3272 C	Formula
UX-TW 51.76	
UX-325 39.85	
UX-230 8.39	

PANTONE 3282 C	Formula
UX-325 47.36	
UX-TW 38.54	
UX-230 11.67	
UX-114 2.43	

PANTONE 3292 C	Formula
UX-325 58.25	
UX-TW 24.29	
UX-SB 17.01	
UX-066 0.45	

PANTONE 3302 C	Formula
UX-325 47.36	
UX-SB 26.47	
UX-TW 25.81	
UX-066 0.36	

PANTONE 3245 C	Formula
UX-TW 95.25	
UX-325 4.14	
UX-230 0.61	

PANTONE 3255 C	Formula
UX-TW 88.17	
UX-325 10.82	
UX-230 1.01	

PANTONE 3265 C	Formula
UX-TW 47.60	
UX-MX 28.20	
UX-325 22.10	
UX-230 2.10	

PANTONE 3275 C	Formula
UX-325 42.24	
UX-TW 33.88	
UX-MX 19.09	
UX-230 4.79	

PANTONE 3285 C	Formula
UX-325 48.43	
UX-TW 43.67	
UX-230 5.22	
UX-114 2.68	

PANTONE 3295 C	Formula
UX-325 50.99	
UX-TW 37.13	
UX-230 6.58	
UX-114 5.30	

PANTONE 3305 C	Formula
UX-325 47.78	
UX-TW 26.03	
UX-SB 25.25	
UX-066 0.94	

PANTONE 3248 C	Formula
UX-TW 91.63	
UX-230 3.49	
UX-064 2.50	
UX-325 2.38	

Plastical UX

PANTONE 3258 C	Formula
UX-TW	82.09
UX-230	6.61
UX-325	6.47
UX-064	4.83

PANTONE 3268 C	Formula
UX-TW	62.17
UX-325	20.53
UX-230	10.59
UX-064	6.71

PANTONE 3278 C	Formula
UX-325	37.77
UX-TW	36.35
UX-230	15.94
UX-064	9.94

PANTONE 3288 C	Formula
UX-230	33.55
UX-TW	28.07
UX-064	20.36
UX-325	18.02

PANTONE 3298 C	Formula
UX-325	31.63
UX-230	21.61
UX-TW	21.53
UX-066	18.03
UX-SB	7.20

PANTONE 3308 C	Formula
UX-064	31.08
UX-230	26.94
UX-SB	23.31
UX-TW	18.67

PANTONE 331 C	Formula
UX-TW	96.94
UX-325	3.06

PANTONE 332 C	Formula
UX-TW	94.56
UX-325	5.44

PANTONE 333 C	Formula
UX-TW	87.94
UX-325	11.49
UX-066	0.57

PANTONE 334 C	Formula
UX-325	65.96
UX-TW	21.93
UX-MX	8.14
UX-SB	2.44
UX-064	1.53

PANTONE 335 C	Formula
UX-325	73.56
UX-TW	15.61
UX-121	6.52
UX-066	4.31

PANTONE 336 C	Formula
UX-325	70.95
UX-TW	14.07
UX-121	11.43
UX-066	3.55

PANTONE 337 C	Formula
UX-TW	93.08
UX-064	2.99
UX-230	2.43
UX-325	1.50

PANTONE 338 C	Formula
UX-TW	88.31
UX-064	4.71
UX-230	4.06
UX-325	2.92

PANTONE 339 C	Formula
UX-TW	59.18
UX-325	19.30
UX-064	12.32
UX-230	9.20

PANTONE 340 C	Formula
UX-325	37.08
UX-TW	21.59
UX-064	18.40
UX-230	15.90
UX-MX	7.03

Plastical UX

PANTONE 341 C	Formula
UX-066	32.11
UX-230	30.28
UX-325	19.24
UX-TW	18.37

PANTONE 342 C	Formula
UX-064	42.47
UX-230	32.89
UX-TW	15.01
UX-SB	9.63

PANTONE 343 C	Formula
UX-064	37.34
UX-230	26.94
UX-SB	21.43
UX-TW	14.29

PANTONE 3375 C	Formula
UX-TW	91.58
UX-325	7.14
UX-064	1.28

PANTONE 3385 C	Formula
UX-TW	81.22
UX-325	15.52
UX-064	3.26

PANTONE 3395 C	Formula
UX-TW	34.30
UX-MX	34.08
UX-325	26.81
UX-064	4.81

PANTONE 3405 C	Formula
UX-325	54.49
UX-MX	19.54
UX-TW	17.48
UX-064	8.49

PANTONE 3415 C	Formula
UX-325	81.82
UX-114	10.08
UX-TW	6.77
UX-064	1.33

PANTONE 3425 C	Formula
UX-325	69.39
UX-TW	10.69
UX-066	10.50
UX-121	9.42

PANTONE 3435 C	Formula
UX-064	41.10
UX-230	23.50
UX-SB	18.70
UX-TW	16.70

PANTONE 344 C	Formula
UX-TW	94.45
UX-064	2.97
UX-325	1.47
UX-230	1.11

PANTONE 345 C	Formula
UX-TW	90.05
UX-064	5.36
UX-230	2.46
UX-325	2.13

PANTONE 346 C	Formula
UX-TW	82.23
UX-064	9.27
UX-325	4.81
UX-230	3.69

PANTONE 347 C	Formula
UX-325	37.39
UX-064	30.51
UX-TW	21.12
UX-230	10.98

PANTONE 348 C	Formula
UX-064	51.03
UX-230	26.45
UX-TW	16.65
UX-325	5.87

PANTONE 349 C	Formula
UX-064	49.77
UX-230	25.36
UX-TW	15.83
UX-SB	9.04

Plastical UX

PANTONE 350 C	Formula
UX-064 37.51	
UX-SB 26.15	
UX-TW 21.19	
UX-230 15.15	

PANTONE 351 C	Formula
UX-TW 93.28	
UX-325 3.69	
UX-064 3.03	

PANTONE 352 C	Formula
UX-TW 89.69	
UX-325 5.57	
UX-064 4.74	

PANTONE 353 C	Formula
UX-TW 85.25	
UX-325 8.17	
UX-064 6.58	

PANTONE 354 C	Formula
UX-325 48.41	
UX-064 31.19	
UX-TW 11.94	
UX-MX 8.46	

PANTONE 355 C	Formula
UX-325 53.20	
UX-064 31.50	
UX-TW 13.80	
UX-SB 1.50	

PANTONE 356 C	Formula
UX-325 50.00	
UX-064 29.60	
UX-TW 13.00	
UX-SB 7.40	

PANTONE 357 C	Formula
UX-064 46.49	
UX-TW 24.53	
UX-230 14.81	
UX-SB 14.17	

PANTONE 358 C	Formula
UX-TW 84.72	
UX-064 11.56	
UX-325 2.62	
UX-230 1.10	

PANTONE 359 C	Formula
UX-TW 80.82	
UX-064 14.54	
UX-325 3.48	
UX-230 1.16	

PANTONE 360 C	Formula
UX-TW 50.13	
UX-064 37.23	
UX-325 9.86	
UX-230 2.78	

PANTONE 361 C	Formula
UX-064 54.98	
UX-TW 24.95	
UX-325 14.24	
UX-230 5.83	

PANTONE 362 C	Formula
UX-064 65.18	
UX-TW 21.15	
UX-230 12.28	
UX-165 1.39	

PANTONE 363 C	Formula
UX-064 65.75	
UX-TW 20.53	
UX-230 12.19	
UX-127 1.53	

PANTONE 364 C	Formula
UX-064 67.99	
UX-TW 16.02	
UX-230 12.69	
UX-127 3.30	

PANTONE 365 C	Formula
UX-TW 88.87	
UX-064 9.40	
UX-325 1.73	

Plastical UX

PANTONE 366 C	Formula
UX-TW	83.85
UX-064	13.60
UX-325	2.55

PANTONE 367 C	Formula
UX-TW	69.52
UX-064	25.44
UX-325	5.04

PANTONE 368 C	Formula
UX-064	67.20
UX-TW	18.59
UX-325	10.19
UX-230	4.02

PANTONE 369 C	Formula
UX-064	73.67
UX-TW	17.25
UX-230	8.91
UX-127	0.17

PANTONE 370 C	Formula
UX-064	71.20
UX-TW	17.40
UX-230	7.40
UX-SB	4.00

PANTONE 371 C	Formula
UX-064	58.30
UX-TW	22.30
UX-SB	14.10
UX-230	5.30

PANTONE 372 C	Formula
UX-TW	82.97
UX-064	15.42
UX-325	1.61

PANTONE 373 C	Formula
UX-TW	73.61
UX-064	24.03
UX-325	2.36

PANTONE 374 C	Formula
UX-TW	61.63
UX-064	34.95
UX-325	3.42

PANTONE 375 C	Formula
UX-064	74.58
UX-TW	15.98
UX-325	9.44

PANTONE 376 C	Formula
UX-064	74.32
UX-TW	13.05
UX-325	11.41
UX-165	1.22

PANTONE 377 C	Formula
UX-064	72.41
UX-325	13.45
UX-TW	11.75
UX-127	2.39

PANTONE 378 C	Formula
UX-064	58.28
UX-SB	19.83
UX-TW	13.47
UX-325	8.42

PANTONE 379 C	Formula
UX-TW	70.45
UX-064	28.26
UX-325	1.29

PANTONE 380 C	Formula
UX-TW	56.67
UX-064	41.37
UX-325	1.96

PANTONE 381 C	Formula
UX-064	54.78
UX-TW	42.52
UX-325	2.70

Plastical UX

PANTONE 382 C	Formula
UX-064 62.97	
UX-TW 25.79	
UX-MX 7.66	
UX-325 3.58	

PANTONE 383 C	Formula
UX-064 78.79	
UX-TW 15.79	
UX-230 3.31	
UX-165 2.11	

PANTONE 384 C	Formula
UX-064 76.88	
UX-TW 15.11	
UX-165 4.10	
UX-230 3.91	

PANTONE 385 C	Formula
UX-064 68.69	
UX-TW 17.29	
UX-325 8.50	
UX-127 5.52	

PANTONE 386 C	Formula
UX-TW 71.18	
UX-064 28.05	
UX-325 0.77	

PANTONE 387 C	Formula
UX-TW 55.43	
UX-064 43.36	
UX-325 1.21	

PANTONE 388 C	Formula
UX-064 61.96	
UX-TW 36.32	
UX-325 1.72	

PANTONE 389 C	Formula
UX-064 72.15	
UX-TW 25.52	
UX-325 2.33	

PANTONE 390 C	Formula
UX-064 79.94	
UX-TW 15.95	
UX-325 3.57	
UX-127 0.54	

PANTONE 391 C	Formula
UX-064 77.66	
UX-TW 15.32	
UX-325 4.78	
UX-127 2.24	

PANTONE 392 C	Formula
UX-064 80.73	
UX-TW 7.75	
UX-325 7.14	
UX-127 4.38	

PANTONE 393 C	Formula
UX-TW 86.90	
UX-064 12.83	
UX-325 0.27	

PANTONE 394 C	Formula
UX-TW 53.50	
UX-064 45.70	
UX-325 0.80	

PANTONE 395 C	Formula
UX-064 66.82	
UX-TW 32.02	
UX-325 1.16	

PANTONE 396 C	Formula
UX-064 91.98	
UX-TW 6.49	
UX-325 1.53	

PANTONE 397 C	Formula
UX-064 90.25	
UX-TW 6.37	
UX-325 2.66	
UX-127 0.72	

Plastical UX

PANTONE 398 C	Formula
UX-064 88.80	
UX-TW 6.20	
UX-325 3.60	
UX-127 1.40	

PANTONE 399 C	Formula
UX-064 83.40	
UX-TW 9.90	
UX-SB 5.70	
UX-230 1.00	

PANTONE 3935 C	Formula
UX-TW 74.43	
UX-064 25.25	
UX-325 0.32	

PANTONE 3945 C	Formula
UX-064 79.40	
UX-TW 19.89	
UX-325 0.71	

PANTONE 3955 C	Formula
UX-064 95.32	
UX-TW 3.81	
UX-325 0.87	

PANTONE 3965 C	Formula
UX-064 98.92	
UX-325 1.08	

PANTONE 3975 C	Formula
UX-064 83.83	
UX-TW 10.87	
UX-165 3.21	
UX-230 2.09	

PANTONE 3985 C	Formula
UX-064 80.06	
UX-TW 12.09	
UX-325 4.64	
UX-127 3.21	

PANTONE 3995 C	Formula
UX-064 67.36	
UX-SB 20.82	
UX-TW 10.52	
UX-165 1.30	

PANTONE 400 C	Formula
UX-TW 96.67	
UX-SB 2.20	
UX-066 0.75	
UX-164 0.38	

PANTONE 401 C	Formula
UX-TW 93.31	
UX-SB 4.32	
UX-066 2.00	
UX-164 0.37	

PANTONE 402 C	Formula
UX-TW 89.68	
UX-SB 6.92	
UX-066 2.91	
UX-164 0.49	

PANTONE 403 C	Formula
UX-TW 74.21	
UX-066 16.71	
UX-325 4.97	
UX-127 4.11	

PANTONE 404 C	Formula
UX-TW 59.47	
UX-066 26.25	
UX-325 7.89	
UX-127 6.39	

PANTONE 405 C	Formula
UX-066 41.13	
UX-TW 35.15	
UX-325 13.25	
UX-127 10.47	

PANTONE 406 C	Formula
UX-TW 96.04	
UX-SB 2.46	
UX-066 0.90	
UX-164 0.60	

Plastical UX

PANTONE 407 C	Formula
UX-TW 86.80	
UX-066 8.43	
UX-325 2.45	
UX-127 2.32	

PANTONE 408 C	Formula
UX-TW 80.19	
UX-066 12.84	
UX-325 3.50	
UX-127 3.47	

PANTONE 409 C	Formula
UX-TW 76.01	
UX-066 15.48	
UX-127 4.29	
UX-325 4.22	

PANTONE 410 C	Formula
UX-TW 60.78	
UX-066 25.35	
UX-127 6.99	
UX-325 6.88	

PANTONE 411 C	Formula
UX-TW 40.69	
UX-066 37.71	
UX-127 10.82	
UX-325 10.78	

PANTONE 412 C	Formula
UX-SB 53.06	
UX-066 19.64	
UX-TW 19.06	
UX-164 8.24	

PANTONE 413 C	Formula
UX-TW 96.13	
UX-SB 2.59	
UX-066 1.08	
UX-325 0.20	

PANTONE 414 C	Formula
UX-TW 93.90	
UX-SB 3.82	
UX-066 1.82	
UX-325 0.46	

PANTONE 415 C	Formula
UX-TW 82.80	
UX-066 10.40	
UX-325 4.20	
UX-127 2.60	

PANTONE 416 C	Formula
UX-TW 73.41	
UX-066 16.35	
UX-325 6.33	
UX-127 3.91	

PANTONE 417 C	Formula
UX-TW 59.17	
UX-066 25.12	
UX-325 9.77	
UX-127 5.94	

PANTONE 418 C	Formula
UX-TW 43.81	
UX-066 34.19	
UX-325 13.73	
UX-127 8.27	

PANTONE 419 C	Formula
UX-066 48.61	
UX-325 26.90	
UX-127 18.05	
UX-TW 6.44	

PANTONE 420 C	Formula
UX-TW 97.63	
UX-SB 2.37	

PANTONE 421 C	Formula
UX-TW 96.04	
UX-SB 3.96	

PANTONE 422 C	Formula
UX-TW 89.38	
UX-066 6.99	
UX-230 1.89	
UX-127 1.74	

Plastical UX

PANTONE 423 C	Formula
UX-TW	82.17
UX-066	11.70
UX-230	3.23
UX-127	2.90

PANTONE 424 C	Formula
UX-TW	71.38
UX-066	19.16
UX-230	4.93
UX-127	4.53

PANTONE 425 C	Formula
UX-TW	51.83
UX-066	31.94
UX-230	8.34
UX-127	7.89

PANTONE 426 C	Formula
UX-SB	61.70
UX-TW	19.62
UX-064	15.00
UX-127	3.68

PANTONE 427 C	Formula
UX-TW	99.23
UX-SB	0.48
UX-127	0.16
UX-230	0.13

PANTONE 428 C	Formula
UX-TW	97.93
UX-SB	1.72
UX-230	0.22
UX-127	0.13

PANTONE 429 C	Formula
UX-TW	94.42
UX-SB	5.15
UX-230	0.43

PANTONE 430 C	Formula
UX-TW	82.51
UX-066	10.99
UX-230	3.54
UX-127	2.96

PANTONE 431 C	Formula
UX-TW	61.32
UX-066	24.35
UX-230	8.07
UX-127	6.26

PANTONE 432 C	Formula
UX-066	39.16
UX-TW	36.33
UX-230	13.64
UX-127	10.87

PANTONE 433 C	Formula
UX-SB	70.11
UX-230	13.22
UX-TW	10.28
UX-127	6.39

PANTONE 434 C	Formula
UX-TW	97.51
UX-121	1.05
UX-325	0.94
UX-165	0.50

PANTONE 435 C	Formula
UX-TW	95.39
UX-121	2.46
UX-325	1.88
UX-165	0.27

PANTONE 436 C	Formula
UX-TW	89.08
UX-121	5.99
UX-325	4.58
UX-165	0.35

PANTONE 437 C	Formula
UX-TW	69.38
UX-121	16.44
UX-325	12.95
UX-114	1.23

PANTONE 438 C	Formula
UX-121	37.60
UX-325	35.50
UX-TW	22.83
UX-165	4.07

Plastical UX

PANTONE 439 C	Formula
UX-325 40.94	
UX-121 37.92	
UX-TW 14.57	
UX-165 6.57	

PANTONE 440 C	Formula
UX-325 38.25	
UX-164 36.30	
UX-114 18.81	
UX-TW 6.64	

PANTONE 441 C	Formula
UX-TW 95.95	
UX-325 2.15	
UX-121 1.90	

PANTONE 442 C	Formula
UX-TW 92.74	
UX-325 4.22	
UX-121 3.04	

PANTONE 443 C	Formula
UX-TW 93.80	
UX-SB 5.00	
UX-325 1.20	

PANTONE 444 C	Formula
UX-TW 76.14	
UX-325 13.96	
UX-121 9.15	
UX-114 0.75	

PANTONE 445 C	Formula
UX-TW 40.42	
UX-325 35.77	
UX-121 23.25	
UX-114 0.56	

PANTONE 446 C	Formula
UX-TW 44.21	
UX-SB 31.11	
UX-114 12.56	
UX-325 12.12	

PANTONE 447 C	Formula
UX-TW 33.67	
UX-SB 33.33	
UX-114 16.94	
UX-325 16.06	

PANTONE WARM GRAY 1 C	Formula
UX-TW 98.33	
UX-SB 0.91	
UX-066 0.59	
UX-121 0.17	

PANTONE WARM GRAY 2 C	Formula
UX-TW 97.03	
UX-SB 1.91	
UX-066 0.83	
UX-121 0.23	

PANTONE WARM GRAY 3 C	Formula
UX-TW 95.22	
UX-SB 3.30	
UX-066 1.20	
UX-121 0.28	

PANTONE WARM GRAY 4 C	Formula
UX-TW 94.48	
UX-SB 3.72	
UX-066 1.47	
UX-121 0.33	

PANTONE WARM GRAY 5 C	Formula
UX-TW 92.41	
UX-SB 5.12	
UX-066 2.04	
UX-121 0.43	

PANTONE WARM GRAY 6 C	Formula
UX-TW 86.29	
UX-066 8.83	
UX-325 2.57	
UX-127 2.31	

PANTONE WARM GRAY 7 C	Formula
UX-TW 82.78	
UX-066 11.10	
UX-325 3.17	
UX-127 2.95	

Plastical UX

PANTONE WARM GRAY 8 C	Formula
UX-TW 77.30	
UX-066 14.84	
UX-325 4.08	
UX-127 3.78	

PANTONE WARM GRAY 9 C	Formula
UX-TW 72.41	
UX-066 18.21	
UX-325 4.86	
UX-127 4.52	

PANTONE WARM GRAY 10 C	Formula
UX-TW 67.53	
UX-066 21.40	
UX-325 5.75	
UX-127 5.32	

PANTONE WARM GRAY 11 C	Formula
UX-TW 51.71	
UX-066 31.67	
UX-325 8.75	
UX-127 7.87	

PANTONE COOL GRAY 1 C	Formula
UX-TW 99.33	
UX-SB 0.67	

PANTONE COOL GRAY 2 C	Formula
UX-TW 98.48	
UX-SB 1.42	
UX-127 0.10	

PANTONE COOL GRAY 3 C	Formula
UX-TW 97.59	
UX-SB 2.31	
UX-064 0.10	

PANTONE COOL GRAY 4 C	Formula
UX-TW 96.61	
UX-SB 3.08	
UX-064 0.31	

PANTONE COOL GRAY 5 C	Formula
UX-TW 95.32	
UX-SB 4.11	
UX-064 0.42	
UX-127 0.15	

PANTONE COOL GRAY 6 C	Formula
UX-TW 94.91	
UX-SB 4.53	
UX-064 0.42	
UX-127 0.14	

PANTONE COOL GRAY 7 C	Formula
UX-TW 93.15	
UX-SB 6.21	
UX-064 0.50	
UX-127 0.14	

PANTONE COOL GRAY 8 C	Formula
UX-TW 81.24	
UX-066 12.36	
UX-230 3.21	
UX-127 3.19	

PANTONE COOL GRAY 9 C	Formula
UX-TW 78.49	
UX-066 14.23	
UX-127 3.66	
UX-230 3.62	

PANTONE COOL GRAY 10 C	Formula
UX-TW 68.55	
UX-066 20.87	
UX-127 5.32	
UX-230 5.26	

PANTONE COOL GRAY 11 C	Formula
UX-TW 57.84	
UX-066 27.81	
UX-127 7.18	
UX-230 7.17	

PANTONE 448 C	Formula
UX-064 43.30	
UX-SB 27.65	
UX-TW 25.50	
UX-127 3.55	

Plastical UX

PANTONE 449 C	Formula
UX-064 62.99	
UX-127 12.88	
UX-TW 12.65	
UX-325 11.48	

PANTONE 450 C	Formula
UX-064 63.86	
UX-TW 14.72	
UX-127 11.52	
UX-325 9.90	

PANTONE 451 C	Formula
UX-TW 78.64	
UX-064 17.35	
UX-127 2.46	
UX-230 1.55	

PANTONE 452 C	Formula
UX-TW 87.09	
UX-064 10.40	
UX-127 1.51	
UX-230 1.00	

PANTONE 453 C	Formula
UX-TW 93.28	
UX-064 5.34	
UX-127 0.82	
UX-230 0.56	

PANTONE 454 C	Formula
UX-TW 96.26	
UX-064 2.97	
UX-127 0.46	
UX-230 0.31	

PANTONE 4485 C	Formula
UX-064 55.64	
UX-SB 26.20	
UX-TW 11.82	
UX-165 6.34	

PANTONE 4495 C	Formula
UX-064 58.87	
UX-TW 30.34	
UX-127 6.05	
UX-325 4.74	

PANTONE 4505 C	Formula
UX-TW 54.02	
UX-064 39.17	
UX-127 3.74	
UX-325 3.07	

PANTONE 4515 C	Formula
UX-TW 75.36	
UX-064 21.06	
UX-127 1.97	
UX-325 1.61	

PANTONE 4525 C	Formula
UX-TW 88.05	
UX-064 10.08	
UX-127 1.06	
UX-325 0.81	

PANTONE 4535 C	Formula
UX-TW 94.03	
UX-064 4.58	
UX-SB 1.19	
UX-127 0.20	

PANTONE 4545 C	Formula
UX-TW 97.06	
UX-064 2.30	
UX-SB 0.47	
UX-127 0.17	

PANTONE 455 C	Formula
UX-064 62.50	
UX-SB 19.80	
UX-TW 14.55	
UX-165 3.15	

PANTONE 456 C	Formula
UX-064 74.95	
UX-TW 18.10	
UX-127 3.74	
UX-325 3.21	

PANTONE 457 C	Formula
UX-064 70.12	
UX-TW 22.14	
UX-165 5.80	
UX-230 1.94	

Plastical UX

PANTONE 458 C	Formula
UX-TW	71.49
UX-064	26.51
UX-165	1.44
UX-230	0.56

PANTONE 459 C	Formula
UX-TW	83.35
UX-064	15.40
UX-165	0.89
UX-230	0.36

PANTONE 460 C	Formula
UX-TW	89.61
UX-064	9.53
UX-165	0.62
UX-230	0.24

PANTONE 461 C	Formula
UX-TW	93.88
UX-064	5.66
UX-165	0.33
UX-230	0.13

PANTONE 462 C	Formula
UX-064	54.31
UX-165	28.15
UX-230	9.24
UX-TW	8.30

PANTONE 463 C	Formula
UX-064	57.94
UX-165	25.86
UX-TW	9.48
UX-230	6.72

PANTONE 464 C	Formula
UX-064	60.55
UX-165	22.32
UX-TW	12.39
UX-230	4.74

PANTONE 465 C	Formula
UX-TW	73.45
UX-064	19.47
UX-165	5.63
UX-230	1.45

PANTONE 466 C	Formula
UX-TW	85.59
UX-064	10.25
UX-165	3.26
UX-230	0.90

PANTONE 467 C	Formula
UX-TW	88.96
UX-064	7.69
UX-165	2.64
UX-230	0.71

PANTONE 468 C	Formula
UX-TW	93.93
UX-064	4.13
UX-165	1.51
UX-230	0.43

PANTONE 4625 C	Formula
UX-SB	38.76
UX-114	38.01
UX-TW	12.27
UX-164	10.96

PANTONE 4635 C	Formula
UX-TW	40.12
UX-066	37.89
UX-SB	12.24
UX-121	9.75

PANTONE 4645 C	Formula
UX-TW	69.17
UX-066	19.03
UX-SB	6.57
UX-121	5.23

PANTONE 4655 C	Formula
UX-TW	84.15
UX-066	9.02
UX-SB	3.82
UX-121	3.01

PANTONE 4665 C	Formula
UX-TW	92.56
UX-066	3.85
UX-SB	2.02
UX-121	1.57

Plastical UX

PANTONE 4675 C		Formula
UX-TW	95.68	
UX-066	2.29	
UX-SB	1.07	
UX-121	0.96	

PANTONE 4685 C		Formula
UX-TW	97.64	
UX-066	1.17	
UX-121	0.64	
UX-SB	0.55	

PANTONE 469 C		Formula
UX-066	47.28	
UX-SB	22.37	
UX-TW	15.18	
UX-121	15.17	

PANTONE 470 C		Formula
UX-066	48.65	
UX-TW	26.39	
UX-121	15.91	
UX-SB	9.05	

PANTONE 471 C		Formula
UX-066	50.29	
UX-TW	28.72	
UX-121	16.05	
UX-SB	4.94	

PANTONE 472 C		Formula
UX-TW	85.54	
UX-066	10.09	
UX-121	3.48	
UX-SB	0.89	

PANTONE 473 C		Formula
UX-TW	93.33	
UX-066	4.47	
UX-121	1.89	
UX-SB	0.31	

PANTONE 474 C		Formula
UX-TW	95.72	
UX-066	2.84	
UX-121	1.25	
UX-SB	0.19	

PANTONE 475 C		Formula
UX-TW	94.96	
UX-066	4.04	
UX-121	0.90	
UX-SB	0.10	

PANTONE 4695 C		Formula
UX-164	33.81	
UX-064	30.61	
UX-SB	25.66	
UX-TW	9.92	

PANTONE 4705 C		Formula
UX-TW	32.43	
UX-064	31.53	
UX-164	22.14	
UX-SB	13.90	

PANTONE 4715 C		Formula
UX-TW	59.32	
UX-064	21.08	
UX-165	11.88	
UX-SB	7.72	

PANTONE 4725 C		Formula
UX-TW	81.48	
UX-064	8.87	
UX-165	5.48	
UX-SB	4.17	

PANTONE 4735 C		Formula
UX-TW	89.95	
UX-064	4.51	
UX-165	3.10	
UX-SB	2.44	

PANTONE 4745 C		Formula
UX-TW	93.88	
UX-064	2.74	
UX-165	1.82	
UX-SB	1.56	

PANTONE 4755 C		Formula
UX-TW	97.02	
UX-064	1.34	
UX-165	1.05	
UX-SB	0.59	

Plastical UX

PANTONE 476 C	Formula
UX-064	47.03
UX-165	39.11
UX-230	10.95
UX-TW	2.91

PANTONE 477 C	Formula
UX-064	32.60
UX-164	28.10
UX-TW	21.60
UX-SB	17.70

PANTONE 478 C	Formula
UX-064	47.13
UX-165	40.14
UX-TW	6.42
UX-230	6.31

PANTONE 479 C	Formula
UX-TW	69.77
UX-064	21.16
UX-127	4.30
UX-MX	3.90
UX-165	0.87

PANTONE 480 C	Formula
UX-TW	85.74
UX-064	7.39
UX-MX	4.79
UX-127	1.92
UX-165	0.16

PANTONE 481 C	Formula
UX-TW	89.57
UX-MX	6.79
UX-064	2.68
UX-127	0.74
UX-165	0.22

PANTONE 482 C	Formula
UX-TW	97.46
UX-064	1.82
UX-127	0.45
UX-165	0.27

PANTONE 483 C	Formula
UX-064	37.47
UX-165	36.69
UX-SB	20.74
UX-TW	5.10

PANTONE 484 C	Formula
UX-165	48.88
UX-064	43.18
UX-325	5.18
UX-TW	2.76

PANTONE 485 C	Formula
UX-165	50.75
UX-114	45.88
UX-TW	3.37

PANTONE 486 C	Formula
UX-TW	75.50
UX-064	14.10
UX-165	10.25
UX-121	0.15

PANTONE 487 C	Formula
UX-TW	88.25
UX-064	7.07
UX-165	4.29
UX-127	0.39

PANTONE 488 C	Formula
UX-TW	92.69
UX-064	4.44
UX-165	2.52
UX-127	0.35

PANTONE 489 C	Formula
UX-TW	95.50
UX-064	2.45
UX-165	2.05

PANTONE 490 C	Formula
UX-121	44.28
UX-SB	29.65
UX-TW	21.54
UX-165	4.53

PANTONE 491 C	Formula
UX-121	49.05
UX-TW	25.72
UX-SB	19.82
UX-165	5.41

Plastical UX

PANTONE 492 C	Formula
UX-121 49.80	
UX-TW 31.74	
UX-SB 12.36	
UX-165 6.10	

PANTONE 493 C	Formula
UX-TW 85.92	
UX-121 10.84	
UX-165 2.30	
UX-230 0.94	

PANTONE 494 C	Formula
UX-TW 95.94	
UX-121 2.30	
UX-165 1.76	

PANTONE 495 C	Formula
UX-TW 96.83	
UX-121 1.81	
UX-165 1.36	

PANTONE 496 C	Formula
UX-TW 97.83	
UX-165 1.14	
UX-121 1.03	

PANTONE 497 C	Formula
UX-164 33.47	
UX-114 25.59	
UX-325 25.10	
UX-SB 9.41	
UX-TW 6.43	

PANTONE 498 C	Formula
UX-164 34.56	
UX-114 31.83	
UX-325 18.33	
UX-TW 15.28	

PANTONE 499 C	Formula
UX-114 37.83	
UX-164 31.79	
UX-TW 15.26	
UX-325 15.12	

PANTONE 500 C	Formula
UX-TW 84.93	
UX-121 11.49	
UX-325 2.51	
UX-165 1.07	

PANTONE 501 C	Formula
UX-TW 95.98	
UX-121 2.78	
UX-165 0.75	
UX-325 0.49	

PANTONE 502 C	Formula
UX-TW 97.14	
UX-121 1.89	
UX-165 0.72	
UX-325 0.25	

PANTONE 503 C	Formula
UX-TW 98.54	
UX-121 0.78	
UX-165 0.68	

PANTONE 4975 C	Formula
UX-SB 41.81	
UX-121 36.78	
UX-TW 12.87	
UX-165 8.54	

PANTONE 4985 C	Formula
UX-TW 55.46	
UX-121 26.91	
UX-SB 16.48	
UX-114 1.15	

PANTONE 4995 C	Formula
UX-TW 75.18	
UX-121 13.54	
UX-SB 9.81	
UX-114 1.47	

PANTONE 5005 C	Formula
UX-TW 87.55	
UX-121 6.17	
UX-SB 5.38	
UX-114 0.90	

Plastical UX

PANTONE 5015 C	Formula
UX-TW	94.44
UX-121	3.08
UX-SB	2.48

PANTONE 5025 C	Formula
UX-TW	96.62
UX-121	1.94
UX-SB	1.44

PANTONE 5035 C	Formula
UX-TW	98.40
UX-121	0.90
UX-SB	0.70

PANTONE 504 C	Formula
UX-121	35.24
UX-SB	32.94
UX-TW	19.17
UX-165	12.65

PANTONE 505 C	Formula
UX-121	56.51
UX-165	17.25
UX-TW	14.73
UX-230	11.51

PANTONE 506 C	Formula
UX-121	49.06
UX-165	23.23
UX-TW	19.81
UX-230	7.90

PANTONE 507 C	Formula
UX-TW	87.43
UX-121	7.19
UX-165	4.48
UX-230	0.90

PANTONE 508 C	Formula
UX-TW	93.20
UX-121	3.78
UX-165	2.40
UX-230	0.62

PANTONE 509 C	Formula
UX-TW	96.98
UX-165	1.84
UX-121	1.18

PANTONE 510 C	Formula
UX-TW	97.72
UX-165	1.49
UX-121	0.79

PANTONE 511 C	Formula
UX-165	43.15
UX-325	22.93
UX-121	21.41
UX-TW	12.51

PANTONE 512 C	Formula
UX-165	62.31
UX-TW	20.26
UX-325	10.56
UX-121	6.87

PANTONE 513 C	Formula
UX-165	68.83
UX-TW	25.03
UX-325	6.14

PANTONE 514 C	Formula
UX-TW	87.17
UX-165	12.28
UX-230	0.55

PANTONE 515 C	Formula
UX-TW	92.61
UX-165	7.25
UX-230	0.14

PANTONE 516 C	Formula
UX-TW	96.01
UX-165	3.80
UX-127	0.19

Plastical UX

PANTONE 517 C	Formula
UX-TW	97.42
UX-165	2.38
UX-127	0.20

PANTONE 5115 C	Formula
UX-164	32.60
UX-TW	30.60
UX-SB	26.50
UX-165	10.30

PANTONE 5125 C	Formula
UX-165	40.92
UX-TW	34.71
UX-066	17.17
UX-230	7.20

PANTONE 5135 C	Formula
UX-TW	69.88
UX-164	23.47
UX-230	3.98
UX-064	2.67

PANTONE 5145 C	Formula
UX-TW	84.33
UX-164	11.57
UX-230	2.28
UX-064	1.82

PANTONE 5155 C	Formula
UX-TW	95.04
UX-164	3.70
UX-230	0.66
UX-SB	0.60

PANTONE 5165 C	Formula
UX-TW	98.21
UX-165	0.96
UX-SB	0.55
UX-127	0.16
UX-230	0.12

PANTONE 5175 C	Formula
UX-TW	99.12
UX-165	0.34
UX-SB	0.32
UX-127	0.22

PANTONE 518 C	Formula
UX-165	50.24
UX-325	21.77
UX-066	15.25
UX-TW	12.74

PANTONE 519 C	Formula
UX-165	57.05
UX-325	18.57
UX-TW	16.25
UX-066	8.13

PANTONE 520 C	Formula
UX-165	60.26
UX-TW	20.76
UX-325	15.04
UX-066	3.94

PANTONE 521 C	Formula
UX-TW	81.68
UX-165	13.78
UX-064	2.34
UX-230	2.20

PANTONE 522 C	Formula
UX-TW	88.13
UX-165	8.72
UX-064	1.60
UX-230	1.55

PANTONE 523 C	Formula
UX-TW	95.66
UX-165	3.65
UX-230	0.69

PANTONE 524 C	Formula
UX-TW	99.04
UX-127	0.66
UX-165	0.30

PANTONE 5185 C	Formula
UX-TW	39.12
UX-SB	28.51
UX-114	22.07
UX-127	10.30

Plastical UX

PANTONE 5195 C	Formula
UX-TW	40.73
UX-165	28.03
UX-SB	23.81
UX-114	7.43

PANTONE 5205 C	Formula
UX-TW	68.41
UX-165	13.75
UX-114	12.35
UX-230	5.49

PANTONE 5215 C	Formula
UX-TW	85.74
UX-165	5.76
UX-114	5.75
UX-230	2.75

PANTONE 5225 C	Formula
UX-TW	94.20
UX-066	3.30
UX-127	1.90
UX-SB	0.60

PANTONE 5235 C	Formula
UX-TW	97.61
UX-SB	1.34
UX-165	0.95
UX-127	0.10

PANTONE 5245 C	Formula
UX-TW	99.18
UX-SB	0.36
UX-165	0.30
UX-127	0.16

PANTONE 525 C	Formula
UX-TW	45.00
UX-164	22.50
UX-127	13.00
UX-MX	10.40
UX-SB	9.10

PANTONE 526 C	Formula
UX-TW	48.05
UX-165	28.16
UX-127	19.23
UX-066	4.56

PANTONE 527 C	Formula
UX-TW	33.60
UX-MX	30.40
UX-165	19.60
UX-127	16.40

PANTONE 528 C	Formula
UX-TW	90.40
UX-127	5.05
UX-165	4.55

PANTONE 529 C	Formula
UX-TW	97.14
UX-127	2.12
UX-165	0.74

PANTONE 530 C	Formula
UX-TW	98.17
UX-127	1.43
UX-165	0.40

PANTONE 531 C	Formula
UX-TW	99.00
UX-127	0.80
UX-165	0.20

PANTONE 5255 C	Formula
UX-TW	34.50
UX-066	31.40
UX-127	26.00
UX-230	8.10

PANTONE 5265 C	Formula
UX-TW	52.31
UX-127	20.76
UX-066	19.60
UX-230	7.33

PANTONE 5275 C	Formula
UX-TW	67.00
UX-066	14.43
UX-127	12.47
UX-230	6.10

Plastical UX

PANTONE 5285 C	Formula
UX-TW	85.43
UX-066	7.03
UX-127	4.81
UX-230	2.73

PANTONE 5295 C	Formula
UX-TW	94.65
UX-114	2.51
UX-230	1.68
UX-127	1.16

PANTONE 5305 C	Formula
UX-TW	96.59
UX-114	1.52
UX-230	1.13
UX-127	0.76

PANTONE 5315 C	Formula
UX-TW	99.00
UX-SB	0.40
UX-127	0.30
UX-230	0.30

PANTONE 532 C	Formula
UX-066	33.23
UX-TW	30.85
UX-325	18.33
UX-127	17.59

PANTONE 533 C	Formula
UX-165	42.23
UX-325	32.50
UX-TW	19.29
UX-066	5.98

PANTONE 534 C	Formula
UX-165	42.86
UX-325	35.86
UX-TW	19.12
UX-066	2.16

PANTONE 535 C	Formula
UX-TW	92.16
UX-127	2.86
UX-325	2.84
UX-064	2.14

PANTONE 536 C	Formula
UX-TW	95.14
UX-325	1.85
UX-127	1.68
UX-064	1.33

PANTONE 537 C	Formula
UX-TW	97.17
UX-165	1.43
UX-230	0.81
UX-SB	0.59

PANTONE 538 C	Formula
UX-TW	98.99
UX-SB	0.38
UX-127	0.33
UX-230	0.30

PANTONE 539 C	Formula
UX-230	46.60
UX-066	27.15
UX-TW	14.60
UX-127	11.65

PANTONE 540 C	Formula
UX-230	61.42
UX-066	15.07
UX-TW	14.04
UX-127	9.47

PANTONE 541 C	Formula
UX-230	64.98
UX-TW	20.22
UX-127	8.24
UX-064	6.56

PANTONE 542 C	Formula
UX-TW	86.77
UX-230	8.77
UX-127	2.28
UX-064	2.18

PANTONE 543 C	Formula
UX-TW	94.60
UX-230	3.15
UX-064	1.16
UX-127	1.09

Plastical UX

PANTONE 544 C	Formula
UX-TW 98.00	
UX-230 1.50	
UX-127 0.50	

PANTONE 545 C	Formula
UX-TW 98.78	
UX-230 0.90	
UX-127 0.32	

PANTONE 5395 C	Formula
UX-164 36.28	
UX-230 27.80	
UX-066 18.06	
UX-TW 17.86	

PANTONE 5405 C	Formula
UX-TW 57.26	
UX-064 19.23	
UX-230 15.67	
UX-127 7.84	

PANTONE 5415 C	Formula
UX-TW 74.16	
UX-064 11.96	
UX-230 8.91	
UX-127 4.97	

PANTONE 5425 C	Formula
UX-TW 87.13	
UX-064 6.28	
UX-230 4.01	
UX-127 2.58	

PANTONE 5435 C	Formula
UX-TW 93.74	
UX-064 3.18	
UX-230 1.83	
UX-127 1.25	

PANTONE 5445 C	Formula
UX-TW 96.93	
UX-064 1.53	
UX-230 0.93	
UX-127 0.61	

PANTONE 5455 C	Formula
UX-TW 99.11	
UX-230 0.38	
UX-SB 0.31	
UX-127 0.20	

PANTONE 546 C	Formula
UX-230 36.65	
UX-164 34.94	
UX-066 26.06	
UX-TW 2.35	

PANTONE 547 C	Formula
UX-230 48.15	
UX-164 27.49	
UX-066 22.26	
UX-TW 2.10	

PANTONE 548 C	Formula
UX-164 43.72	
UX-230 42.50	
UX-064 10.63	
UX-TW 3.15	

PANTONE 549 C	Formula
UX-TW 79.33	
UX-230 11.48	
UX-064 6.52	
UX-127 2.67	

PANTONE 550 C	Formula
UX-TW 89.85	
UX-230 4.79	
UX-064 3.86	
UX-127 1.50	

PANTONE 551 C	Formula
UX-TW 95.10	
UX-230 2.29	
UX-064 1.78	
UX-127 0.83	

PANTONE 552 C	Formula
UX-TW 98.12	
UX-230 0.96	
UX-066 0.61	
UX-127 0.31	

Plastical UX

PANTONE 5463 C	Formula
UX-SB	29.64
UX-325	26.38
UX-TW	23.23
UX-230	20.75

PANTONE 5473 C	Formula
UX-TW	56.80
UX-230	21.60
UX-066	12.00
UX-SB	9.60

PANTONE 5483 C	Formula
UX-TW	81.48
UX-230	8.39
UX-SB	5.46
UX-066	4.67

PANTONE 5493 C	Formula
UX-TW	92.62
UX-SB	2.90
UX-230	2.88
UX-066	1.60

PANTONE 5503 C	Formula
UX-TW	95.39
UX-230	1.83
UX-066	1.59
UX-SB	0.91
UX-127	0.28

PANTONE 5513 C	Formula
UX-TW	98.23
UX-230	0.78
UX-066	0.77
UX-127	0.22

PANTONE 5523 C	Formula
UX-TW	98.88
UX-230	0.51
UX-066	0.45
UX-127	0.16

PANTONE 5467 C	Formula
UX-064	54.05
UX-230	21.76
UX-127	14.81
UX-TW	9.38

PANTONE 5477 C	Formula
UX-064	39.83
UX-TW	36.97
UX-230	14.48
UX-127	8.72

PANTONE 5487 C	Formula
UX-TW	69.32
UX-064	19.94
UX-230	6.45
UX-127	4.29

PANTONE 5497 C	Formula
UX-TW	86.67
UX-064	8.44
UX-230	2.82
UX-127	2.07

PANTONE 5507 C	Formula
UX-TW	92.57
UX-064	4.55
UX-230	1.65
UX-127	1.23

PANTONE 5517 C	Formula
UX-TW	94.78
UX-064	3.09
UX-230	1.13
UX-127	1.00

PANTONE 5527 C	Formula
UX-TW	97.69
UX-064	1.40
UX-230	0.53
UX-127	0.38

PANTONE 553 C	Formula
UX-SB	32.81
UX-064	30.34
UX-TW	19.22
UX-230	17.63

PANTONE 554 C	Formula
UX-064	36.50
UX-TW	29.20
UX-230	20.60
UX-SB	13.70

Plastical UX

PANTONE 555 C	Formula
UX-064	34.98
UX-TW	25.07
UX-230	23.20
UX-SB	16.75

PANTONE 556 C	Formula
UX-TW	79.36
UX-064	13.28
UX-230	5.76
UX-127	1.60

PANTONE 557 C	Formula
UX-TW	89.12
UX-064	6.90
UX-230	3.08
UX-127	0.90

PANTONE 558 C	Formula
UX-TW	93.36
UX-064	4.12
UX-230	1.97
UX-127	0.55

PANTONE 559 C	Formula
UX-TW	96.97
UX-064	1.77
UX-230	0.97
UX-127	0.29

PANTONE 5535 C	Formula
UX-SB	40.74
UX-325	34.28
UX-TW	13.62
UX-066	11.36

PANTONE 5545 C	Formula
UX-TW	46.24
UX-066	24.92
UX-325	22.99
UX-127	5.85

PANTONE 5555 C	Formula
UX-TW	71.68
UX-066	12.94
UX-325	11.93
UX-127	3.45

PANTONE 5565 C	Formula
UX-TW	82.44
UX-325	10.56
UX-121	5.00
UX-066	2.00

PANTONE 5575 C	Formula
UX-TW	90.57
UX-325	5.40
UX-121	2.68
UX-066	1.35

PANTONE 5585 C	Formula
UX-TW	93.92
UX-325	3.59
UX-121	1.76
UX-066	0.73

PANTONE 5595 C	Formula
UX-TW	97.09
UX-325	1.94
UX-121	0.97

PANTONE 560 C	Formula
UX-325	61.24
UX-121	21.70
UX-TW	12.88
UX-066	4.18

PANTONE 561 C	Formula
UX-325	54.87
UX-TW	30.58
UX-121	10.29
UX-114	4.26

PANTONE 562 C	Formula
UX-TW	47.75
UX-325	43.90
UX-121	5.78
UX-114	2.57

PANTONE 563 C	Formula
UX-TW	89.16
UX-325	8.41
UX-114	2.08
UX-127	0.35

Plastical UX

PANTONE 564 C	Formula
UX-TW	93.33
UX-325	5.14
UX-114	1.24
UX-127	0.29

PANTONE 565 C	Formula
UX-TW	96.50
UX-064	1.80
UX-230	1.50
UX-165	0.20

PANTONE 566 C	Formula
UX-TW	98.37
UX-230	0.76
UX-064	0.72
UX-165	0.15

PANTONE 5605 C	Formula
UX-SB	48.09
UX-064	28.04
UX-230	20.66
UX-TW	3.21

PANTONE 5615 C	Formula
UX-064	41.41
UX-TW	40.43
UX-230	10.71
UX-127	7.45

PANTONE 5625 C	Formula
UX-TW	64.53
UX-064	24.71
UX-230	6.23
UX-127	4.53

PANTONE 5635 C	Formula
UX-TW	84.31
UX-064	10.90
UX-230	2.74
UX-127	2.05

PANTONE 5645 C	Formula
UX-TW	91.58
UX-064	5.68
UX-230	1.56
UX-127	1.18

PANTONE 5655 C	Formula
UX-TW	94.79
UX-064	3.46
UX-230	1.03
UX-127	0.72

PANTONE 5665 C	Formula
UX-TW	97.20
UX-064	1.87
UX-230	0.56
UX-127	0.37

PANTONE 567 C	Formula
UX-325	58.50
UX-TW	17.90
UX-121	17.30
UX-066	6.30

PANTONE 568 C	Formula
UX-325	54.03
UX-TW	35.26
UX-121	5.55
UX-114	5.16

PANTONE 569 C	Formula
UX-325	58.00
UX-TW	34.20
UX-121	5.30
UX-066	2.50

PANTONE 570 C	Formula
UX-TW	90.14
UX-325	8.36
UX-114	1.27
UX-127	0.23

PANTONE 571 C	Formula
UX-TW	94.88
UX-325	4.35
UX-114	0.62
UX-127	0.15

PANTONE 572 C	Formula
UX-TW	97.58
UX-325	2.20
UX-165	0.22

Plastical UX

PANTONE 573 C	Formula
UX-TW 98.60	
UX-325 1.40	

PANTONE 574 C	Formula
UX-064 67.01	
UX-TW 17.35	
UX-230 8.87	
UX-127 6.77	

PANTONE 575 C	Formula
UX-064 67.15	
UX-TW 19.56	
UX-230 9.35	
UX-127 3.94	

PANTONE 576 C	Formula
UX-064 62.71	
UX-TW 27.90	
UX-230 7.60	
UX-127 1.79	

PANTONE 577 C	Formula
UX-TW 85.14	
UX-064 12.73	
UX-230 1.64	
UX-127 0.49	

PANTONE 578 C	Formula
UX-TW 88.82	
UX-064 9.55	
UX-230 1.29	
UX-127 0.34	

PANTONE 579 C	Formula
UX-TW 91.79	
UX-064 7.00	
UX-230 0.92	
UX-127 0.29	

PANTONE 580 C	Formula
UX-TW 95.70	
UX-064 3.73	
UX-230 0.47	
UX-127 0.10	

PANTONE 5743 C	Formula
UX-064 48.02	
UX-SB 34.05	
UX-TW 11.92	
UX-230 6.01	

PANTONE 5753 C	Formula
UX-064 42.94	
UX-TW 32.12	
UX-SB 21.19	
UX-230 3.75	

PANTONE 5763 C	Formula
UX-064 47.07	
UX-TW 42.58	
UX-230 5.48	
UX-127 4.87	

PANTONE 5773 C	Formula
UX-TW 70.11	
UX-064 24.38	
UX-230 2.90	
UX-127 2.61	

PANTONE 5783 C	Formula
UX-TW 82.10	
UX-064 14.60	
UX-230 1.68	
UX-127 1.62	

PANTONE 5793 C	Formula
UX-TW 89.65	
UX-064 8.44	
UX-127 0.96	
UX-230 0.95	

PANTONE 5803 C	Formula
UX-TW 94.80	
UX-064 4.21	
UX-230 0.51	
UX-127 0.48	

PANTONE 5747 C	Formula
UX-064 48.35	
UX-SB 34.91	
UX-325 8.96	
UX-TW 7.78	

Plastical UX

PANTONE 5757 C	Formula
UX-064	56.02
UX-TW	20.28
UX-SB	18.20
UX-325	5.50

PANTONE 5767 C	Formula
UX-TW	56.35
UX-064	31.95
UX-SB	9.40
UX-325	2.30

PANTONE 5777 C	Formula
UX-TW	74.83
UX-064	17.79
UX-SB	6.00
UX-325	1.38

PANTONE 5787 C	Formula
UX-TW	90.67
UX-064	6.20
UX-SB	2.56
UX-325	0.57

PANTONE 5797 C	Formula
UX-TW	93.78
UX-064	4.28
UX-SB	1.54
UX-325	0.40

PANTONE 5807 C	Formula
UX-TW	96.07
UX-064	2.85
UX-SB	0.86
UX-325	0.22

PANTONE 581 C	Formula
UX-064	69.03
UX-SB	19.48
UX-TW	11.39
UX-127	0.10

PANTONE 582 C	Formula
UX-064	76.41
UX-TW	13.18
UX-165	6.21
UX-230	4.20

PANTONE 583 C	Formula
UX-064	80.26
UX-TW	15.53
UX-230	2.44
UX-165	1.77

PANTONE 584 C	Formula
UX-TW	64.59
UX-064	34.25
UX-230	0.87
UX-165	0.29

PANTONE 585 C	Formula
UX-TW	79.09
UX-064	20.16
UX-325	0.52
UX-230	0.23

PANTONE 586 C	Formula
UX-TW	85.38
UX-064	14.00
UX-325	0.48
UX-230	0.14

PANTONE 587 C	Formula
UX-TW	92.73
UX-064	6.94
UX-325	0.33

PANTONE 5815 C	Formula
UX-064	55.73
UX-SB	28.34
UX-TW	15.39
UX-127	0.54

PANTONE 5825 C	Formula
UX-064	58.05
UX-TW	26.42
UX-SB	15.42
UX-127	0.11

PANTONE 5835 C	Formula
UX-TW	66.60
UX-064	26.68
UX-SB	6.45
UX-230	0.27

Plastical UX

PANTONE 5845 C UX-TW 78.73 UX-064 16.67 UX-SB 4.42 UX-230 0.18	Formula	PANTONE 5855 C UX-TW 90.08 UX-064 7.61 UX-SB 2.21 UX-230 0.10	Formula	PANTONE 5865 C UX-TW 93.64 UX-064 4.76 UX-SB 1.50 UX-230 0.10	Formula	PANTONE 5875 C UX-TW 95.88 UX-064 3.17 UX-SB 0.95	Formula
PANTONE 600 C UX-TW 94.00 UX-064 6.00	Formula	PANTONE 601 C UX-TW 91.22 UX-064 8.78	Formula	PANTONE 602 C UX-TW 85.37 UX-064 14.50 UX-325 0.13	Formula	PANTONE 603 C UX-TW 74.20 UX-064 25.52 UX-325 0.28	Formula
PANTONE 604 C UX-TW 62.54 UX-064 37.03 UX-325 0.43	Formula	PANTONE 605 C UX-064 84.08 UX-TW 13.86 UX-325 1.06 UX-165 1.00	Formula	PANTONE 606 C UX-064 90.70 UX-TW 7.00 UX-165 1.50 UX-230 0.80	Formula	PANTONE 607 C UX-TW 97.91 UX-064 2.09	Formula
PANTONE 608 C UX-TW 95.34 UX-064 4.54 UX-165 0.12	Formula	PANTONE 609 C UX-TW 89.36 UX-064 10.25 UX-165 0.20 UX-230 0.19	Formula	PANTONE 610 C UX-TW 78.48 UX-064 20.52 UX-165 0.58 UX-230 0.42	Formula	PANTONE 611 C UX-TW 55.75 UX-064 42.11 UX-165 1.28 UX-230 0.86	Formula

Plastical UX

PANTONE 612 C	Formula
UX-064 69.79	
UX-TW 26.18	
UX-165 2.53	
UX-230 1.50	

PANTONE 613 C	Formula
UX-064 77.39	
UX-TW 16.10	
UX-165 4.24	
UX-230 2.27	

PANTONE 614 C	Formula
UX-TW 96.15	
UX-064 3.50	
UX-127 0.21	
UX-325 0.14	

PANTONE 615 C	Formula
UX-TW 95.19	
UX-064 4.28	
UX-127 0.28	
UX-325 0.25	

PANTONE 616 C	Formula
UX-TW 92.27	
UX-064 6.93	
UX-127 0.41	
UX-325 0.39	

PANTONE 617 C	Formula
UX-TW 83.90	
UX-064 14.46	
UX-325 0.85	
UX-127 0.79	

PANTONE 618 C	Formula
UX-TW 65.81	
UX-064 31.00	
UX-325 1.69	
UX-127 1.50	

PANTONE 619 C	Formula
UX-064 60.79	
UX-TW 32.88	
UX-325 3.34	
UX-127 2.99	

PANTONE 620 C	Formula
UX-064 64.99	
UX-TW 27.14	
UX-325 4.17	
UX-127 3.70	

PANTONE 621 C	Formula
UX-TW 98.40	
UX-325 0.85	
UX-066 0.56	
UX-127 0.19	

PANTONE 622 C	Formula
UX-TW 94.96	
UX-066 2.25	
UX-325 2.23	
UX-127 0.56	

PANTONE 623 C	Formula
UX-TW 87.78	
UX-066 5.57	
UX-325 5.40	
UX-127 1.25	

PANTONE 624 C	Formula
UX-TW 78.40	
UX-325 10.19	
UX-066 9.14	
UX-127 2.27	

PANTONE 625 C	Formula
UX-TW 58.36	
UX-325 20.18	
UX-066 17.30	
UX-127 4.16	

PANTONE 626 C	Formula
UX-325 46.45	
UX-066 32.14	
UX-TW 11.24	
UX-127 10.17	

PANTONE 627 C	Formula
UX-325 40.75	
UX-SB 39.61	
UX-066 15.53	
UX-127 4.11	

Plastical UX

PANTONE 628 C	Formula
UX-TW 98.96	
UX-230 1.04	

PANTONE 629 C	Formula
UX-TW 98.06	
UX-230 1.94	

PANTONE 630 C	Formula
UX-TW 95.85	
UX-230 3.58	
UX-SB 0.31	
UX-066 0.26	

PANTONE 631 C	Formula
UX-TW 90.53	
UX-230 7.57	
UX-066 1.32	
UX-SB 0.58	

PANTONE 632 C	Formula
UX-TW 77.23	
UX-230 15.89	
UX-325 5.04	
UX-SB 1.84	

PANTONE 633 C	Formula
UX-TW 49.40	
UX-230 36.25	
UX-325 11.39	
UX-SB 2.96	

PANTONE 634 C	Formula
UX-230 64.45	
UX-TW 15.74	
UX-325 12.15	
UX-SB 7.66	

PANTONE 635 C	Formula
UX-TW 98.50	
UX-230 1.50	

PANTONE 636 C	Formula
UX-TW 97.34	
UX-230 2.66	

PANTONE 637 C	Formula
UX-TW 94.84	
UX-230 5.16	

PANTONE 638 C	Formula
UX-TW 71.08	
UX-MX 15.26	
UX-230 11.69	
UX-325 1.97	

PANTONE 639 C	Formula
UX-TW 54.64	
UX-230 24.19	
UX-MX 16.63	
UX-325 4.54	

PANTONE 640 C	Formula
UX-TW 50.86	
UX-230 41.25	
UX-325 7.89	

PANTONE 641 C	Formula
UX-230 54.50	
UX-TW 26.20	
UX-MX 12.40	
UX-325 6.90	

PANTONE 642 C	Formula
UX-TW 98.60	
UX-230 0.70	
UX-SB 0.38	
UX-127 0.32	

PANTONE 643 C	Formula
UX-TW 98.25	
UX-230 0.90	
UX-SB 0.43	
UX-127 0.42	

Plastical UX

PANTONE 644 C	Formula
UX-TW 92.05	
UX-230 3.10	
UX-064 3.02	
UX-127 1.83	

PANTONE 645 C	Formula
UX-TW 86.97	
UX-230 5.62	
UX-064 4.46	
UX-127 2.95	

PANTONE 646 C	Formula
UX-TW 79.37	
UX-230 9.49	
UX-064 6.50	
UX-127 4.64	

PANTONE 647 C	Formula
UX-TW 48.14	
UX-230 28.43	
UX-064 13.23	
UX-127 10.20	

PANTONE 648 C	Formula
UX-230 43.29	
UX-066 21.67	
UX-TW 18.78	
UX-127 16.26	

PANTONE 649 C	Formula
UX-TW 98.78	
UX-230 0.55	
UX-127 0.37	
UX-SB 0.30	

PANTONE 650 C	Formula
UX-TW 97.89	
UX-230 0.95	
UX-SB 0.59	
UX-127 0.57	

PANTONE 651 C	Formula
UX-TW 94.40	
UX-230 2.35	
UX-SB 2.06	
UX-127 1.19	

PANTONE 652 C	Formula
UX-TW 85.62	
UX-230 6.83	
UX-SB 4.57	
UX-127 2.98	

PANTONE 653 C	Formula
UX-TW 58.16	
UX-230 24.83	
UX-SB 8.98	
UX-127 8.03	

PANTONE 654 C	Formula
UX-230 48.92	
UX-066 22.03	
UX-127 20.65	
UX-TW 8.40	

PANTONE 655 C	Formula
UX-230 43.75	
UX-127 25.33	
UX-SB 15.65	
UX-066 15.27	

PANTONE 656 C	Formula
UX-TW 98.73	
UX-230 0.66	
UX-127 0.41	
UX-SB 0.20	

PANTONE 657 C	Formula
UX-TW 97.75	
UX-230 1.30	
UX-127 0.75	
UX-SB 0.20	

PANTONE 658 C	Formula
UX-TW 95.34	
UX-230 2.75	
UX-127 1.43	
UX-SB 0.48	

PANTONE 659 C	Formula
UX-TW 89.13	
UX-230 5.17	
UX-127 4.08	
UX-SB 1.62	

Plastical UX

PANTONE 660 C	Formula
UX-TW 69.92	
UX-230 22.09	
UX-127 6.77	
UX-SB 1.22	

PANTONE 661 C	Formula
UX-230 44.77	
UX-TW 41.93	
UX-127 11.93	
UX-SB 1.37	

PANTONE 662 C	Formula
UX-230 64.27	
UX-127 19.28	
UX-TW 12.00	
UX-SB 4.45	

PANTONE 663 C	Formula
UX-TW 99.11	
UX-127 0.46	
UX-SB 0.32	
UX-230 0.11	

PANTONE 664 C	Formula
UX-TW 98.50	
UX-SB 0.77	
UX-127 0.62	
UX-230 0.11	

PANTONE 665 C	Formula
UX-TW 97.11	
UX-SB 1.70	
UX-127 1.07	
UX-230 0.12	

PANTONE 666 C	Formula
UX-TW 93.87	
UX-SB 3.62	
UX-127 2.37	
UX-230 0.14	

PANTONE 667 C	Formula
UX-TW 84.12	
UX-SB 8.68	
UX-127 7.08	
UX-230 0.12	

PANTONE 668 C	Formula
UX-TW 69.41	
UX-127 16.34	
UX-SB 9.57	
UX-114 4.68	

PANTONE 669 C	Formula
UX-TW 48.52	
UX-127 31.24	
UX-SB 14.46	
UX-114 5.78	

PANTONE 670 C	Formula
UX-TW 98.40	
UX-165 1.20	
UX-127 0.20	
UX-064 0.20	

PANTONE 671 C	Formula
UX-TW 97.47	
UX-165 1.98	
UX-064 0.29	
UX-127 0.26	

PANTONE 672 C	Formula
UX-TW 93.12	
UX-165 5.23	
UX-064 1.09	
UX-127 0.56	

PANTONE 673 C	Formula
UX-TW 87.09	
UX-165 10.42	
UX-064 1.80	
UX-127 0.69	

PANTONE 674 C	Formula
UX-TW 74.25	
UX-165 21.73	
UX-064 2.99	
UX-127 1.03	

PANTONE 675 C	Formula
UX-165 50.48	
UX-TW 42.14	
UX-121 5.64	
UX-325 1.74	

Plastical UX

PANTONE 676 C	Formula
UX-165	71.00
UX-TW	15.50
UX-121	10.00
UX-325	3.50

PANTONE 677 C	Formula
UX-TW	98.43
UX-165	1.29
UX-SB	0.28

PANTONE 678 C	Formula
UX-TW	97.70
UX-165	1.79
UX-SB	0.51

PANTONE 679 C	Formula
UX-TW	95.86
UX-165	3.04
UX-SB	0.79
UX-064	0.31

PANTONE 680 C	Formula
UX-TW	89.35
UX-165	7.57
UX-SB	1.88
UX-064	1.20

PANTONE 681 C	Formula
UX-TW	69.39
UX-165	22.85
UX-SB	4.32
UX-064	3.44

PANTONE 682 C	Formula
UX-TW	50.18
UX-165	38.06
UX-SB	5.95
UX-064	5.81

PANTONE 683 C	Formula
UX-165	55.24
UX-121	20.52
UX-TW	12.77
UX-325	11.47

PANTONE 684 C	Formula
UX-TW	97.01
UX-165	2.14
UX-114	0.58
UX-325	0.27

PANTONE 685 C	Formula
UX-TW	94.99
UX-165	3.32
UX-114	1.01
UX-325	0.68

PANTONE 686 C	Formula
UX-TW	91.41
UX-165	5.60
UX-114	1.84
UX-325	1.15

PANTONE 687 C	Formula
UX-TW	80.93
UX-165	12.48
UX-114	3.96
UX-325	2.63

PANTONE 688 C	Formula
UX-TW	65.90
UX-165	22.92
UX-114	6.75
UX-325	4.43

PANTONE 689 C	Formula
UX-165	41.58
UX-TW	38.89
UX-114	11.37
UX-325	8.16

PANTONE 690 C	Formula
UX-165	52.56
UX-114	18.88
UX-325	17.24
UX-TW	11.32

PANTONE 691 C	Formula
UX-TW	98.63
UX-121	0.90
UX-SB	0.33
UX-165	0.14

Plastical UX

PANTONE 692 C	Formula
UX-TW	95.91
UX-121	2.59
UX-SB	1.37
UX-165	0.13

PANTONE 693 C	Formula
UX-TW	93.93
UX-121	3.69
UX-SB	2.10
UX-165	0.28

PANTONE 694 C	Formula
UX-TW	89.08
UX-121	6.56
UX-SB	3.67
UX-165	0.69

PANTONE 695 C	Formula
UX-TW	70.60
UX-121	16.84
UX-SB	7.06
UX-165	5.50

PANTONE 696 C	Formula
UX-TW	44.92
UX-121	30.17
UX-165	14.36
UX-SB	10.55

PANTONE 697 C	Formula
UX-121	37.26
UX-TW	33.56
UX-165	15.44
UX-SB	13.74

PANTONE 698 C	Formula
UX-TW	98.30
UX-121	1.06
UX-165	0.54
UX-SB	0.10

PANTONE 699 C	Formula
UX-TW	96.29
UX-121	2.64
UX-165	0.75
UX-SB	0.32

PANTONE 700 C	Formula
UX-TW	92.48
UX-121	4.79
UX-165	1.48
UX-SB	1.25

PANTONE 701 C	Formula
UX-TW	84.47
UX-121	9.30
UX-165	4.04
UX-SB	2.19

PANTONE 702 C	Formula
UX-TW	72.17
UX-121	16.41
UX-165	8.78
UX-SB	2.64

PANTONE 703 C	Formula
UX-TW	37.08
UX-121	35.98
UX-165	23.30
UX-SB	3.64

PANTONE 704 C	Formula
UX-121	46.83
UX-165	27.57
UX-TW	19.85
UX-SB	5.75

PANTONE 705 C	Formula
UX-TW	99.00
UX-165	0.90
UX-SB	0.10

PANTONE 706 C	Formula
UX-TW	97.65
UX-121	1.48
UX-165	0.77
UX-SB	0.10

PANTONE 707 C	Formula
UX-TW	94.69
UX-121	3.45
UX-165	1.76
UX-SB	0.10

Plastical UX

PANTONE 708 C	Formula
UX-TW 87.73	
UX-121 8.27	
UX-165 3.90	
UX-SB 0.10	

PANTONE 709 C	Formula
UX-TW 73.23	
UX-121 17.33	
UX-165 9.44	

PANTONE 710 C	Formula
UX-TW 47.33	
UX-121 32.16	
UX-165 20.51	

PANTONE 711 C	Formula
UX-121 44.40	
UX-TW 32.70	
UX-165 22.20	
UX-SB 0.70	

PANTONE 712 C	Formula
UX-TW 96.29	
UX-114 1.92	
UX-066 1.69	
UX-SB 0.10	

PANTONE 713 C	Formula
UX-TW 93.95	
UX-114 3.00	
UX-066 2.89	
UX-SB 0.16	

PANTONE 714 C	Formula
UX-TW 87.47	
UX-114 6.11	
UX-066 6.09	
UX-SB 0.33	

PANTONE 715 C	Formula
UX-TW 70.89	
UX-066 16.50	
UX-114 12.03	
UX-SB 0.58	

PANTONE 716 C	Formula
UX-TW 43.11	
UX-066 34.79	
UX-114 21.07	
UX-SB 1.03	

PANTONE 717 C	Formula
UX-066 49.82	
UX-114 39.85	
UX-TW 8.10	
UX-SB 2.23	

PANTONE 718 C	Formula
UX-114 57.87	
UX-066 33.37	
UX-TW 5.43	
UX-SB 3.33	

PANTONE 719 C	Formula
UX-TW 96.74	
UX-114 1.54	
UX-064 1.36	
UX-SB 0.36	

PANTONE 720 C	Formula
UX-TW 94.77	
UX-114 2.39	
UX-064 2.12	
UX-SB 0.72	

PANTONE 721 C	Formula
UX-TW 88.62	
UX-064 5.51	
UX-114 4.54	
UX-SB 1.33	

PANTONE 722 C	Formula
UX-TW 69.11	
UX-064 17.35	
UX-114 10.59	
UX-SB 2.95	

PANTONE 723 C	Formula
UX-TW 48.50	
UX-064 29.00	
UX-114 18.00	
UX-SB 4.50	

Plastical UX

PANTONE 724 C	Formula
UX-114	42.14
UX-064	37.06
UX-SB	10.71
UX-TW	10.09

PANTONE 725 C	Formula
UX-114	55.59
UX-064	23.26
UX-SB	14.81
UX-TW	6.34

PANTONE 726 C	Formula
UX-TW	96.80
UX-114	1.30
UX-064	1.30
UX-SB	0.60

PANTONE 727 C	Formula
UX-TW	92.79
UX-064	3.31
UX-114	2.49
UX-SB	1.41

PANTONE 728 C	Formula
UX-TW	87.35
UX-064	6.23
UX-114	4.14
UX-SB	2.28

PANTONE 729 C	Formula
UX-TW	76.66
UX-064	12.01
UX-114	7.43
UX-SB	3.90

PANTONE 730 C	Formula
UX-TW	58.76
UX-064	22.54
UX-114	12.37
UX-SB	6.33

PANTONE 731 C	Formula
UX-114	40.61
UX-064	30.72
UX-SB	17.27
UX-TW	11.40

PANTONE 732 C	Formula
UX-114	45.54
UX-SB	23.27
UX-064	22.75
UX-TW	8.44

PANTONE 7401 C	Formula
UX-TW	97.37
UX-064	1.83
UX-165	0.80

PANTONE 7402 C	Formula
UX-TW	96.25
UX-064	3.38
UX-127	0.37

PANTONE 7403 C	Formula
UX-TW	91.18
UX-064	8.12
UX-127	0.70

PANTONE 7404 C	Formula
UX-TW	76.06
UX-064	23.80
UX-230	0.14

PANTONE 7405 C	Formula
UX-064	66.60
UX-TW	32.56
UX-SB	0.84

PANTONE 7406 C	Formula
UX-064	73.00
UX-TW	24.60
UX-165	1.93
UX-230	0.47

PANTONE 7407 C	Formula
UX-TW	67.65
UX-064	19.90
UX-165	5.73
UX-114	3.86
UX-325	2.86

Plastical UX

PANTONE 7408 C	Formula
UX-TW	52.31
UX-064	44.96
UX-165	2.56
UX-SB	0.17

PANTONE 7409 C	Formula
UX-TW	39.79
UX-064	36.83
UX-MX	20.00
UX-164	3.38

PANTONE 7410 C	Formula
UX-TW	84.04
UX-114	9.72
UX-066	5.91
UX-127	0.33

PANTONE 7411 C	Formula
UX-TW	69.17
UX-064	22.32
UX-165	7.53
UX-SB	0.98

PANTONE 7412 C	Formula
UX-TW	42.21
UX-066	35.54
UX-114	18.84
UX-SB	3.41

PANTONE 7413 C	Formula
UX-064	48.73
UX-TW	33.58
UX-165	16.53
UX-325	1.16

PANTONE 7414 C	Formula
UX-066	52.58
UX-114	25.37
UX-TW	15.75
UX-164	3.21
UX-230	3.09

PANTONE 7415 C	Formula
UX-TW	93.53
UX-164	3.03
UX-064	2.05
UX-165	1.00
UX-SB	0.39

PANTONE 7416 C	Formula
UX-TW	50.24
UX-165	28.88
UX-064	20.88

PANTONE 7417 C	Formula
UX-165	50.33
UX-064	32.79
UX-TW	16.88

PANTONE 7418 C	Formula
UX-TW	44.47
UX-121	34.61
UX-165	18.37
UX-325	2.55

PANTONE 7419 C	Formula
UX-165	45.46
UX-TW	28.74
UX-114	20.75
UX-325	5.05

PANTONE 7420 C	Formula
UX-165	68.22
UX-114	25.68
UX-325	6.10

PANTONE 7421 C	Formula
UX-164	53.08
UX-114	35.60
UX-230	11.32

PANTONE 7422 C	Formula
UX-TW	96.89
UX-165	3.11

PANTONE 7423 C	Formula
UX-TW	66.82
UX-165	25.41
UX-121	7.77

Plastical UX

PANTONE 7424 C	Formula
UX-165 72.36	
UX-MX 20.00	
UX-066 7.64	

PANTONE 7425 C	Formula
UX-165 62.29	
UX-MX 20.00	
UX-114 16.16	
UX-230 1.55	

PANTONE 7426 C	Formula
UX-165 61.56	
UX-114 24.64	
UX-MX 9.14	
UX-SB 4.66	

PANTONE 7427 C	Formula
UX-121 47.17	
UX-164 46.01	
UX-SB 6.82	

PANTONE 7428 C	Formula
UX-164 77.54	
UX-325 16.86	
UX-114 4.13	
UX-TW 1.47	

PANTONE 7429 C	Formula
UX-TW 93.07	
UX-165 6.01	
UX-325 0.82	
UX-064 0.10	

PANTONE 7430 C	Formula
UX-TW 91.24	
UX-165 7.53	
UX-SB 1.23	

PANTONE 7431 C	Formula
UX-TW 77.39	
UX-165 11.92	
UX-164 8.77	
UX-325 1.92	

PANTONE 7432 C	Formula
UX-TW 58.66	
UX-165 21.79	
UX-164 16.82	
UX-325 2.73	

PANTONE 7433 C	Formula
UX-165 61.39	
UX-TW 26.72	
UX-066 7.79	
UX-SB 4.10	

PANTONE 7434 C	Formula
UX-165 83.18	
UX-064 12.77	
UX-230 4.05	

PANTONE 7435 C	Formula
UX-165 75.29	
UX-066 13.93	
UX-SB 10.78	

PANTONE 7436 C	Formula
UX-TW 96.71	
UX-165 3.29	

PANTONE 7437 C	Formula
UX-TW 53.23	
UX-MX 44.45	
UX-127 2.32	

PANTONE 7438 C	Formula
UX-TW 88.73	
UX-165 8.55	
UX-127 2.72	

PANTONE 7439 C	Formula
UX-TW 61.72	
UX-MX 22.72	
UX-165 13.35	
UX-230 2.21	

Plastical UX

PANTONE 7440 C	Formula
UX-TW 82.05	
UX-165 11.88	
UX-127 3.88	
UX-SB 2.19	

PANTONE 7441 C	Formula
UX-TW 66.02	
UX-MX 20.00	
UX-127 13.98	

PANTONE 7442 C	Formula
UX-TW 53.62	
UX-127 26.38	
UX-MX 20.00	

PANTONE 7443 C	Formula
UX-TW 98.38	
UX-127 1.16	
UX-230 0.46	

PANTONE 7444 C	Formula
UX-TW 96.24	
UX-127 2.46	
UX-230 1.30	

PANTONE 7445 C	Formula
UX-TW 94.25	
UX-127 3.72	
UX-325 2.03	

PANTONE 7446 C	Formula
UX-TW 90.45	
UX-127 6.86	
UX-230 2.69	

PANTONE 7447 C	Formula
UX-TW 54.86	
UX-164 20.49	
UX-127 18.11	
UX-230 6.54	

PANTONE 7448 C	Formula
UX-TW 38.44	
UX-164 21.07	
UX-127 20.39	
UX-SB 20.10	

PANTONE 7449 C	Formula
UX-121 47.80	
UX-164 25.17	
UX-230 24.63	
UX-064 2.40	

PANTONE 7450 C	Formula
UX-TW 97.25	
UX-127 1.56	
UX-230 1.19	

PANTONE 7451 C	Formula
UX-TW 91.88	
UX-230 4.86	
UX-127 3.26	

PANTONE 7452 C	Formula
UX-TW 88.18	
UX-127 6.06	
UX-230 5.76	

PANTONE 7453 C	Formula
UX-TW 90.17	
UX-230 6.47	
UX-127 3.36	

PANTONE 7454 C	Formula
UX-TW 51.35	
UX-MX 30.00	
UX-230 9.33	
UX-165 8.72	
UX-064 0.60	

PANTONE 7455 C	Formula
UX-TW 41.12	
UX-MX 30.00	
UX-230 18.39	
UX-127 10.49	

Plastical UX

PANTONE 7456 C	Formula
UX-TW	71.76
UX-MX	11.73
UX-127	8.36
UX-230	8.15

PANTONE 7457 C	Formula
UX-TW	97.86
UX-230	2.14

PANTONE 7458 C	Formula
UX-TW	89.36
UX-230	7.14
UX-165	3.31
UX-064	0.19

PANTONE 7459 C	Formula
UX-TW	79.08
UX-230	16.05
UX-164	4.87

PANTONE 7460 C	Formula
UX-230	47.68
UX-MX	30.00
UX-TW	18.41
UX-325	3.91

PANTONE 7461 C	Formula
UX-TW	58.09
UX-230	35.31
UX-165	6.60

PANTONE 7462 C	Formula
UX-230	33.74
UX-MX	30.00
UX-165	22.64
UX-TW	11.60
UX-064	2.02

PANTONE 7463 C	Formula
UX-165	42.59
UX-230	37.85
UX-SB	19.56

PANTONE 7464 C	Formula
UX-TW	96.50
UX-230	3.08
UX-SB	0.42

PANTONE 7465 C	Formula
UX-TW	57.61
UX-MX	30.00
UX-230	6.58
UX-325	4.34
UX-064	1.47

PANTONE 7466 C	Formula
UX-TW	40.65
UX-MX	30.00
UX-230	15.45
UX-325	13.90

PANTONE 7467 C	Formula
UX-MX	30.00
UX-TW	29.40
UX-230	20.84
UX-325	19.76

PANTONE 7468 C	Formula
UX-TW	51.07
UX-230	44.21
UX-114	4.72

PANTONE 7469 C	Formula
UX-230	66.45
UX-TW	27.17
UX-114	6.38

PANTONE 7470 C	Formula
UX-230	39.68
UX-MX	30.00
UX-165	17.68
UX-064	8.24
UX-TW	4.40

PANTONE 7471 C	Formula
UX-TW	93.89
UX-325	3.44
UX-230	2.67

Plastical UX

PANTONE 7472 C	Formula
UX-TW	88.15
UX-230	9.34
UX-064	1.93
UX-121	0.58

PANTONE 7473 C	Formula
UX-TW	69.85
UX-230	19.48
UX-066	8.01
UX-064	2.66

PANTONE 7474 C	Formula
UX-MX	30.00
UX-230	29.00
UX-TW	21.52
UX-325	13.57
UX-114	5.91

PANTONE 7475 C	Formula
UX-TW	60.74
UX-230	18.99
UX-066	10.89
UX-164	9.38

PANTONE 7476 C	Formula
UX-230	55.40
UX-TW	18.99
UX-114	14.59
UX-066	11.02

PANTONE 7477 C	Formula
UX-230	47.95
UX-TW	26.63
UX-121	20.46
UX-064	4.96

PANTONE 7478 C	Formula
UX-TW	94.23
UX-325	5.22
UX-064	0.55

PANTONE 7479 C	Formula
UX-TW	44.91
UX-MX	30.00
UX-325	19.12
UX-064	5.97

PANTONE 7480 C	Formula
UX-325	36.23
UX-MX	30.00
UX-TW	26.82
UX-064	6.95

PANTONE 7481 C	Formula
UX-325	54.25
UX-MX	30.00
UX-064	15.75

PANTONE 7482 C	Formula
UX-325	55.45
UX-TW	33.73
UX-064	10.82

PANTONE 7483 C	Formula
UX-325	36.31
UX-MX	24.72
UX-SB	19.03
UX-064	12.29
UX-TW	7.65

PANTONE 7484 C	Formula
UX-325	63.14
UX-SB	19.30
UX-TW	12.51
UX-064	5.05

PANTONE 7485 C	Formula
UX-TW	98.41
UX-230	0.70
UX-064	0.64
UX-165	0.25

PANTONE 7486 C	Formula
UX-TW	94.27
UX-064	2.96
UX-325	2.77

PANTONE 7487 C	Formula
UX-TW	52.83
UX-MX	30.00
UX-064	9.68
UX-325	7.49

Plastical UX

PANTONE 7488 C		Formula
UX-TW	36.13	
UX-MX	30.00	
UX-064	20.74	
UX-325	13.13	

PANTONE 7489 C		Formula
UX-TW	40.28	
UX-MX	30.00	
UX-064	20.50	
UX-230	7.66	
UX-165	1.56	

PANTONE 7490 C		Formula
UX-MX	30.00	
UX-TW	28.42	
UX-064	27.61	
UX-230	9.27	
UX-165	4.70	

PANTONE 7491 C		Formula
UX-TW	42.23	
UX-064	40.38	
UX-230	10.67	
UX-121	6.72	

PANTONE 7492 C		Formula
UX-TW	61.93	
UX-MX	30.00	
UX-064	5.66	
UX-230	1.37	
UX-165	1.04	

PANTONE 7493 C		Formula
UX-TW	92.01	
UX-064	5.43	
UX-230	1.63	
UX-127	0.93	

PANTONE 7494 C		Formula
UX-TW	86.11	
UX-064	6.45	
UX-325	5.03	
UX-127	2.41	

PANTONE 7495 C		Formula
UX-TW	30.06	
UX-MX	30.00	
UX-064	29.55	
UX-230	6.46	
UX-121	3.93	

PANTONE 7496 C		Formula
UX-064	50.94	
UX-325	21.62	
UX-TW	17.47	
UX-121	5.68	
UX-165	4.29	

PANTONE 7497 C		Formula
UX-TW	65.49	
UX-SB	19.77	
UX-064	12.97	
UX-121	1.77	

PANTONE 7498 C		Formula
UX-066	24.00	
UX-064	20.90	
UX-165	20.56	
UX-TW	17.94	
UX-230	16.60	

PANTONE 7499 C		Formula
UX-TW	98.29	
UX-064	1.20	
UX-165	0.51	

PANTONE 7500 C		Formula
UX-TW	96.73	
UX-064	2.40	
UX-127	0.67	
UX-325	0.20	

PANTONE 7501 C		Formula
UX-TW	95.20	
UX-064	3.48	
UX-127	1.12	
UX-325	0.20	

PANTONE 7502 C		Formula
UX-TW	90.87	
UX-064	5.66	
UX-127	1.49	
UX-114	1.13	
UX-325	0.85	

PANTONE 7503 C		Formula
UX-TW	45.85	
UX-MX	30.00	
UX-064	12.33	
UX-165	8.48	
UX-230	3.34	

Plastical UX

PANTONE 7504 C	Formula
UX-TW	55.59
UX-164	21.62
UX-064	13.86
UX-325	8.93

PANTONE 7505 C	Formula
UX-TW	41.75
UX-064	21.00
UX-SB	16.47
UX-114	13.57
UX-165	7.21

PANTONE 7506 C	Formula
UX-TW	67.45
UX-MX	30.00
UX-064	1.30
UX-165	1.25

PANTONE 7507 C	Formula
UX-TW	96.22
UX-064	2.36
UX-121	1.42

PANTONE 7508 C	Formula
UX-TW	88.65
UX-064	6.04
UX-165	2.30
UX-114	2.24
UX-230	0.77

PANTONE 7509 C	Formula
UX-TW	79.11
UX-064	11.99
UX-114	4.02
UX-165	3.69
UX-230	1.19

PANTONE 7510 C	Formula
UX-TW	59.43
UX-064	28.72
UX-121	4.83
UX-SB	3.88
UX-114	3.14

PANTONE 7511 C	Formula
UX-MX	30.00
UX-064	25.17
UX-066	16.94
UX-TW	12.65
UX-121	11.70
UX-230	3.54

PANTONE 7512 C	Formula
UX-064	34.34
UX-MX	27.22
UX-114	17.39
UX-165	13.37
UX-325	7.68

PANTONE 7513 C	Formula
UX-TW	75.25
UX-MX	20.00
UX-114	2.22
UX-165	1.49
UX-SB	1.04

PANTONE 7514 C	Formula
UX-TW	85.68
UX-066	6.62
UX-165	3.84
UX-SB	2.06
UX-114	1.80

PANTONE 7515 C	Formula
UX-TW	76.54
UX-114	10.77
UX-164	5.42
UX-064	5.11
UX-230	2.16

PANTONE 7516 C	Formula
UX-114	36.10
UX-064	22.11
UX-TW	21.12
UX-165	14.65
UX-230	6.02

PANTONE 7517 C	Formula
UX-066	58.81
UX-121	24.08
UX-230	9.88
UX-165	7.23

PANTONE 7518 C	Formula
UX-TW	37.69
UX-165	21.42
UX-066	20.45
UX-SB	20.44

PANTONE 7519 C	Formula
UX-TW	37.10
UX-SB	28.50
UX-164	16.28
UX-064	14.59
UX-121	3.53

Plastical UX

PANTONE 7520 C		Formula
UX-TW	95.24	
UX-164	2.23	
UX-114	2.22	
UX-230	0.31	

PANTONE 7521 C		Formula
UX-TW	81.54	
UX-165	10.44	
UX-064	6.38	
UX-230	1.64	

PANTONE 7522 C		Formula
UX-TW	51.47	
UX-165	28.06	
UX-064	18.20	
UX-230	2.27	

PANTONE 7523 C		Formula
UX-TW	44.99	
UX-165	24.86	
UX-066	17.50	
UX-121	7.33	
UX-325	5.32	

PANTONE 7524 C		Formula
UX-TW	46.84	
UX-121	24.93	
UX-164	14.71	
UX-064	7.23	
UX-325	6.29	

PANTONE 7525 C		Formula
UX-TW	48.11	
UX-164	25.75	
UX-064	22.09	
UX-230	4.05	

PANTONE 7526 C		Formula
UX-TW	97.10	
UX-164	1.78	
UX-230	0.79	
UX-064	0.33	

PANTONE 7527 C		Formula
UX-TW	93.97	
UX-066	3.25	
UX-127	1.76	
UX-325	1.02	

PANTONE 7528 C		Formula
UX-TW	92.38	
UX-SB	3.52	
UX-066	2.91	
UX-127	1.19	

PANTONE 7529 C		Formula
UX-TW	82.30	
UX-066	11.97	
UX-127	3.99	
UX-230	1.74	

PANTONE 7530 C		Formula
UX-TW	88.55	
UX-SB	8.23	
UX-114	3.22	

PANTONE 7531 C		Formula
UX-TW	60.87	
UX-066	22.61	
UX-SB	11.67	
UX-127	4.85	

PANTONE 7532 C		Formula
UX-066	45.71	
UX-TW	31.45	
UX-127	13.59	
UX-325	9.25	

PANTONE 7533 C		Formula
UX-066	45.65	
UX-SB	33.93	
UX-TW	14.70	
UX-127	5.72	

PANTONE 7534 C		Formula
UX-TW	97.71	
UX-064	0.98	
UX-127	0.90	
UX-230	0.41	

PANTONE 7535 C		Formula
UX-TW	89.39	
UX-066	4.43	
UX-164	3.97	
UX-230	2.21	

Plastical UX

PANTONE 7536 C	Formula
UX-TW 82.24	
UX-066 8.41	
UX-164 5.89	
UX-230 3.46	

PANTONE 7537 C	Formula
UX-TW 94.28	
UX-SB 4.99	
UX-230 0.73	

PANTONE 7538 C	Formula
UX-TW 81.35	
UX-MX 10.62	
UX-SB 7.04	
UX-230 0.99	

PANTONE 7539 C	Formula
UX-TW 89.00	
UX-SB 10.07	
UX-230 0.93	

PANTONE 7540 C	Formula
UX-TW 46.91	
UX-127 20.74	
UX-064 19.89	
UX-230 12.46	

PANTONE 7541 C	Formula
UX-TW 98.66	
UX-230 0.68	
UX-SB 0.66	

PANTONE 7542 C	Formula
UX-TW 92.85	
UX-165 3.44	
UX-230 2.87	
UX-064 0.84	

PANTONE 7543 C	Formula
UX-TW 73.23	
UX-MX 20.00	
UX-127 2.58	
UX-230 2.30	
UX-064 1.89	

PANTONE 7544 C	Formula
UX-TW 65.80	
UX-MX 20.00	
UX-127 5.14	
UX-230 4.74	
UX-064 4.32	

PANTONE 7545 C	Formula
UX-TW 38.40	
UX-MX 20.00	
UX-230 15.30	
UX-127 14.43	
UX-064 11.87	

PANTONE 7546 C	Formula
UX-164 46.06	
UX-230 29.15	
UX-MX 13.86	
UX-066 10.93	

PANTONE 7547 C	Formula
UX-SB 50.79	
UX-127 39.50	
UX-230 9.71	